METHOD FOR IMMOBILIZING OLIGONUCLEOTIDES EMPLOYING THE CYCLOADDITION BIOCONJUGATION METHOD

5   RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional Application Serial No. 60/201,561, filed May 1, 2000 and U.S. Provisional Application Serial No. 60/265,020, filed January 30, 2001, both entitled "Immobilization of Oligonucleotides Employing the Cycloaddition Bioconjugation Method." This application is also a continuation in part of

10   U.S. Application Serial No. 09/341,337, filed July 8, 1999, which is a 371 filing of International Application No. PCT/US98/00649 (WO 98/30575), filed January 8, 1998, both entitled "Bioconjugation of Macromolecules."

FIELD OF THE INVENTION

15   This invention describes a novel method for immobilizing molecules on a support. Particularly, this invention describes a method for immobilizing biomolecules on a support using cycloaddition reactions, such as the Diels-Alder reaction.

BACKGROUND OF THE INVENTION

20   Applications for surface immobilized biomolecules are widespread and include nucleic acid sequencing, gene expression profiling, analysis for single nucleotide polymorphisms (SNPs) and evaluation of hapten-antibody or ligand-target interactions. An important subset of these techniques involves immobilization of oligonucleotide probes that employ Watson-Crick hybridization in the interaction with target nucleic

25   acids such as genomic DNA, RNA or cDNA prepared via Polymerase Chain Reaction (PCR) amplification of sample DNA. Current technologies often involve formatting oligonucleotide probes for such analyses into microarrays on glass slides, silicon chips or wafers, micro titer plates or other supports including polyacrylamide gel matrices.

A variety of methods exist for immobilizing biomolecules, including non-covalent

30   (hydrophobic or ionic interactions) as well as covalent methods. A number of these methods are summarized in Table 1. Methods involving covalent attachment are

1

5 generally considered preferable, as more stringent conditions may be applied to the immobilized system for the reduction of non-specific ionic or hydrophobic associations (which raise background signal) without concern for the loss of the probe from the surface. Commonly employed covalent methods include condensation of amines with activated carbonyl groups on the surface, such as activated carboxylic acid esters,

10 carbonates or isocyanates or isothiocyanates. Additionally, amine groups can be condensed with aldehydes under reductive amination conditions to afford secondary amine linkages between the surface and the biomolecule. Furthermore, amines can be condensed with electron deficient heterocycles via nucleophilic aromatic substitution as well as epoxide opening.

15 Cycloaddition reactions can be defined as any reaction between two (or more) moieties (either intra or intermolecular) where the orbitals of the reacting atoms form a cyclic array as the reaction progresses (typically in a concerted fashion although intermediates may be involved) along the reaction coordinate leading to a product. The orbitals involved in this class of reactions are typically π systems although certain σ

20 orbitals can also be involved. The number of electrons associated with this type of reaction are of two types: 4n+2 and 4n, where n = 0, 1, 2, 3, 4, etc. Typical examples of cycloaddition reactions include Diels-Alder cycloaddition reactions, 1,3-dipolar cycloadditions and [2+2] cycloadditions.

  The Diels-Alder reaction, by far the most studied cycloaddition, is the

25 cycloaddition reaction between a conjugated diene and an unsaturated molecule to form a cyclic compound with the π-electrons being used to form the new σ-bonds. The Diels-Alder reaction is an example of [4+2] cycloaddition reaction, as it involves a system of 4π-electrons (the diene) and a system of 2π-(the dienophile). The reaction can be made to occur very rapidly, under mild conditions, and for a wide variety of reactants. The Diels-

30 Alder reaction is broad in scope and is well known to those knowledgeable in the art. A review of the Diels-Alder reaction can be found in "Advanced Organic Chemistry" (March, J., ed.) 839-852 (1992) John Wiley & Sons, NY, which is incorporated herein by reference.

  It has been discovered that the rate of Diels-Alder cycloaddition reactions is

35 enhanced in aqueous solvents. (Rideout and Breslow (1980) J. Am. Chem. Soc.

5   102:7816). (A similar effect is also seen with 1,3-dipolar cycloaddition reactions
(Engberts (1995) Tetrahedron Lett. 36:5389). This enhancement is presumably due to the
hydrophobicity of the diene and dienophile reactants. (Breslow (1991) Acc. Chem. Res.
24:159). This effect extends to intramolecular Diels-Alder reactions. (Blokzijl *et al.*
(1991) J. Am. Chem. Soc. 113:4241). Not only is the reaction rate accelerated in water,

10   but several examples of an increased endo/exo product ratio are also reported. (Breslow
and Maitra (1984) Tetrahedron Lett. 25:1239; Lubineau *et al.* (1990) J. Chem. Soc.
Perkin Trans. I, 3011; Grieco *et al.* (1983) Tetrahedron Lett. 24:1897). Salts which
increase the hydrophobic effect in water, such as lithium chloride (Breslow *et al.* (1983)
Tetrahedron Lett. 24:1901) and also monovalent phosphates (Pai and Smith (1995) J.

15   Org. Chem. 60:3731) have been observed to further accelerate the rate of [4+2]
cycloadditions.

In U.S. Application Serial Nos. 09/051,449, filed April 6, 1998; 08/843,820, filed
April 21, 1997 and 09/402,430, filed October 7, 1999; each entitled "Method for Solution
Phase Synthesis of Oligonucleotides," the Diels-Alder cycloaddition reaction is shown to

20   be an ideal method for anchoring oligonucleotides onto resins. Resins derivatized with a
diene or dienophile are reacted with an oligonucleotide derivatized with a dienophile or
diene, respectively, to yield the Diels-Alder cycloaddition product. In particular, Diels-
Alder reactions between oligonucleotides derivatized with a diene and polymeric resins
derivatized with maleimide groups and with phenyl-triazoline-diones (PTAD) are

25   described. The resulting resins can be used as affinity chromatography resins.

U.S. Application Serial No. 09/341,337, filed July 7, 1999, entitled
"Bioconjugation of Macromolecules," illustrates that cycloaddition reactions in general,
such as the Diels-Alder reaction and 1,3-dipolar cycloaddition reactions, are an ideal
replacement for current methods of conjugating macromolecules with other molecular

30   moieties. The Diels-Alder reaction, in particular, is an ideal method for covalently
linking large water soluble macromolecules with other compounds as the reaction rate is
accelerated in water and can be run at neutral pH. (Rideout and Breslow (1980) J. Am.
Chem. Soc. 102:7816). Additionally, the nature of the reaction allows post-synthetic
modification of the hydrophilic macromolecule without excess reagent or hydrolysis of

35   the reagent. With respect to conjugation to oligonucleotides, this technology has been

5   aided by the ability to efficiently synthesize 2'-O-diene-nucleosides, which allows the

conjugation site to be varied throughout the oligonucleotide or the option of having

multiple conjugation sites.

The present invention describes a method for immobilizing molecules,

particularly biomolecules, to a support using the cycloaddition bioconjugation method.

10   Immobilization of biomolecules via cycloaddition, particularly Diels-Alder reactions,

offers the following major advantages over conventional methods (cf. Table 1):

cycloaddition reactions establish a covalent and stable linkage between the linked

compounds; the reaction proceeds with high chemoselectivity; functional groups of

biomolecules do not interfere with the cycloaddition reaction; the cycloaddition reaction

15   is orthogonal to other immobilization/labeling protocols, thus two-fold reactions are

possible in one reaction mixture; in contrast to general techniques in organic synthesis, as

discussed above, Diels-Alder reactions, can be carried out in aqueous phase, the Diels-

Alder reaction is tremendously accelerated in water and is very fast at room temperature

or slightly below; the cycloaddition reaction proceeds under neutral conditions in a one-

20   step procedure; no by-products are formed during the reaction; no activators or additives

are necessary to run the reaction and the moieties involved in the reaction (dienes and

dienophiles) are stable under various reaction conditions employed for conjugation or

immobilization of biomolecules

Note, that throughout this application various citations are provided. Each citation

25   is specifically incorporated herein by reference in its entirety.

SUMMARY OF THE INVENTION

The present invention describes a novel, chemoselective and highly efficient

method for immobilizing molecules using cycloaddition reactions. The method of the

30   invention offers advantages over existing immobilization methods that can suffer from

cross-reactivity, low selectivity, mechanistic ambiguity and competitive hydrolysis of

reactive groups.

In summary, the method of the instant invention comprises the step of reacting a

derivatized molecule with a derivatized support capable of reacting with said derivatized

35   molecule via a cycloaddition reaction. In a preferred embodiment, the derivatized

4

molecule is a biomolecule, preferably an oligonucleotide, but could also be a hapten, carbohydrate, oligosaccharide, peptide and protein (including an antibody). The support is preferably glass or controlled pore glass (CPG), but could also be polypropylene, polystyrene, polyacrylamide or silicon. In a preferred embodiment, the cycloaddition reaction is a Diels-Alder cycloaddition reaction between the support and the biomolecule. Therefore, the biomolecule is preferably derivatized with one component of a Diels-Alder reaction, i.e., a diene or a dienophile, and the support is derivatized with the appropriate counterpart reactant, i.e., a dienophile or a diene, respectively.

This invention includes a reaction scheme for producing a wide variety of immobilized biomolecules using cycloaddition reactions as typified by the Diels-Alder cycloaddition reaction. The method of this invention can be extended to the immobilization of any molecule, particularly biomolecules on any support that can be appropriately derivatized.

The method of this invention can be extended to all 4n and 4n+2 cycloadditions (where n = 0, 1, 2, 3, 4, etc.). This includes, but is not limited to Diels-Alder cycloadditions, 1,3-dipolar cycloadditions, ene cycloaddition reactions and [2+2] (a 4n type) cycloadditions, such as ketene additions and photochemical [2+2] additions.

Also described herein is a method by which surfaces, preferably glass microscope slides or CPG, may be converted into reactive elements for the cycloaddition immobilization method of the invention by deposition of silane monolayers appropriately functionalized with reaction components for cycloaddition reactions.

Also included in this invention are any novel immobilized and derivatized molecules and derivatized supports produced by the method of the invention.

The method of the invention is applicable to the fields of biomolecule array fabrication for research, development and clinical diagnostic applications relating to nucleic acid sequencing, gene expression profiling, analysis of single nucleotide polymorphisms (SNPs) and evaluation of hapten-antibody or ligand-target interactions.

BRIEF DESCRIPTION OF THE FIGURES

Figure 1 is a fluorescence scan of polyacrylamide gel loaded with 1, 2 and 3 μL of fluorescein labeled compound (26), the synthesis of which is described in Example 6.

Figure 2 is a fluorescence scan of a glass slide showing maleimide functionalization on the lower half of the slide, that was treated with maleimide-silane (19), followed by reaction with a thiol containing-fluorescein reagent (SAMSA-reagent), as described in Example 7.

Figure 3 is a fluorescence scan of maleimide derivatized CPG. In Figure 3A native CPG was first treated with maleimide silane (19), followed by staining with SAMSA-reagent. In Figure 3B native CPG was treated with SAMSA-fluorescein to serve as a control.

Figure 4 is a fluorescence scan of a glass slide showing diene functionalization on the lower half of the slide that was treated with diene-silane reagent (20), followed by reaction of the diene functionalized slide with fluorescein-5-maleimide, as described in Example 8.

Figure 5 is a fluorescence scan of diene functionalized CPG. In Figure 5A CPG was treated with diene-silane (20), followed by staining with fluorescein-5-maleimide. In Figure 5B native CPG was treated with fluorescein-5-maleimide to serve as a control.

Figure 6 shows a diagram of a slide showing placement of septa and contents of septa for demonstration of Diels-Alder surface immobilization of an oligonucleotide on maleimide functionalized glass micro slides as described in Example 9.

Figure 7 illustrates fluorescence scans of glass slides showing successful Diels-Alder surface immobilization of 5'-diene-oligonucleotide (23) on maleimide-functionalized glass micro slides. Slide "1" was pre-treated with 2N NaOH then hot 2N HCl prior to maleimide-functionalization. Slide "2" was pre-treated only with 2N HCl. Spots visible on each slide are where compound (23) came into contact with the maleimide-functionalized portion of the slide prior to hybridization with complementary 5'-fluorescein-oligonucleotide (27); areas of the slides that came into contact with controls showed no response.

Figure 8 illustrates the conjugation of diene-oligonucleotide (23) to maleimide-coated micro titer plates after hybridization with complementary fluorescein labeled sequence 5'-fluorescein-(CA)$_{10}$ (27) (SEQ ID NO:2). Wells 1-3 were treated with diene-oligonucleotide (23), pure, and wells 4-6 were treated with diene-oligonucleotide (23), crude. Wells 1A-6A are the corresponding oligonucleotide (22) controls. Wells 7 and

5   7A are the buffer controls. Wells 1, 1A, 4, 4A were incubated at pH = 5.5, wells 2, 2A,

5, 5A at pH = 6.5 and wells 3, 3A, 6A at pH = 7.7.

Figure 9 illustrates graphically the relation between the loading of CPG (10 mg)

with oligonucleotide (24) and the concentration of oligonucleotide (24) in solution.

Figure 10 illustrates graphically the relation between the loading of CPG (10 mg)

10   with oligonucleotide and the incubation time with oligonucleotide (24).

Figure 11 illustrates fluorescence scans of glass slides showing successful Diels-

Alder surface immobilization of maleimide-oligonucleotide (26) on diene functionalized

glass micro slides. Slide "1" is prior to the wash with phosphate buffered saline (PBS)

illustrating the necessity of the wash to remove non-covalently bound oligonucleotide

15   from the glass surface. Slide "2" is after the PBS wash. The single fluorescent response

visible on the slide is where compound (26) came into contact with the diene-

functionalized portion of slide prior to hybridization with complementary-5'-fluorescein-

oligonucleotide (27). After the PBS wash, areas of the slide that came into contact with

controls showed no response.

20   Figure 12 illustrates fluorescence scans of CPG samples showing Diels-Alder

surface immobilization of an oligonucleotide (maleimide-oligonucleotide (26)) on diene-

functionalized CPG. Figure 12A is prior to the wash with a mixture of 5x0.3 M sodium

citrate and 3 M sodium chloride (SSC) and Figure 12B is after the SSC wash. The

fluorescent response visible on the sample labeled "2A" is where compound (26) came

25   into contact with diene-functionalized CPG prior to hybridization with complementary 5'-

fluorescein-oligonucleotide (27). After the SSC wash, the control samples labeled "2B"

and "2C" showed relatively little response.

Figure 13 is an overlaid Biacore sensorgram illustrating the reproducibility of the

formation of the maleimide-coated BIAcore flow cell surface (37) described in Example

30   15.

Figure 14 is a Biacore sensorgram of the product of the Michael–addition between

maleimide-coated BIAcore flow cell surface (37) and MeO-PEG-SH, which is described

in Example 16.

7

5   Figure 15 is a Biacore sensorgram of the product of the Diels-Alder reaction

between maleimide-coated BIAcore flow cell surface (37) and PEG-diene substrate (34),

described in Example 16.

           Figure 16 is a Biacore sensorgram of the product of the Diels-Alder reaction

between maleimide-coated BIAcore flow cell surface (37) and PEG-anthracene substrate

10   (36), described in Example 17.

           Figure 17 is a Biacore sensorgram of the product of the Diels-Alder reaction

between maleimide-coated BIAcore flow cell surface (37) and cyclohexadiene modified

oligonucleotide (29), described in Example 18.

           Figure 18 is a Biacore sensorgram of the product of the Diels-Alder reaction

15   between maleimide-coated BIAcore flow cell surface (37) and cyclohexadiene modified

oligonucleotide (29), upon hybridization of the immobilized sequence with its

complementary oligonucleotide sequence.

           Figure 19 illustrates the functionalization of glass microscope slides with

anthracene-silane reagent (42).

20

DETAILED DESCRIPTION OF THE INVENTION

           The present invention includes a method for immobilizing molecules on a

support. Specifically, the present invention describes the use of cycloaddition reactions,

in particular the Diels-Alder cycloaddition reaction for the chemoselective

25   immobilization of molecules on a support.

           The method of the instant invention comprises the step of reacting a derivatized

molecule with a derivatized support capable of reacting with said derivatized molecule

via a cycloaddition reaction. In a preferred embodiment, the derivatized molecule is a

biomolecule, most preferably an oligonucleotide and the support is preferably glass or

30   controlled pore glass (CPG). In a preferred embodiment, the cycloaddition reaction is a

Diels-Alder cycloaddition reaction. Therefore, the biomolecule is derivatized with one

component of a Diels-Alder reaction, i.e., a diene or a dienophile, and the support is

derivatized with the appropriate counterpart reactant, i.e., a dienophile or a diene,

respectively.

8

5   This invention includes a reaction scheme for producing a wide variety of

immobilized biomolecules using cycloaddition reactions as typified by the Diels-Alder

cycloaddition reaction. The method of this invention can be used to immobilize any

molecule, particularly biomolecules, on any support that can be appropriately derivatized.

Certain terms used to describe the invention are described herein as follows:

10   "Oligonucleotide" refers to a polynucleotide formed from a plurality of linked

nucleotide units. The nucleotide units each include a nucleoside unit linked together via

a phosphate linking group. The term oligonucleotide also refers to a plurality of

nucleotides that are linked together via linkages other than phosphate linkages such as

phosphorothioate linkages. The oligonucleotide may be naturally occurring or non-

15   naturally occurring. In a preferred embodiment the oligonucleotides of this invention

have between 1-1,000 nucleotides.

For the purposes of this invention "nucleobase" will have the following definition.

A nucleobase is a purine or a pyrimidine base. Nucleobase includes all purines and

pyrimidines currently known to those skilled in the art or any chemical modifications

20   thereof. The purines are attached to the ribose ring through the nitrogen in the 9 position

of the purine ring and the pyrimidines are attached to the ribose ring through the nitrogen

in the 1 position of the pyrimidine ring. The pyrimidine can be modified at the 5- or 6-

position of the pyrimidine ring and the purine can be modified at positions 2-, 6- or 8- of

the purine ring. Certain modifications are described in U.S. Patent Applications Serial

25   No. 08/264,029, filed June 22, 1994, entitled "Novel Method of Preparation of Known

and Novel 2' Modified Pyrimidines Intramolecular Nucleophilic Displacement" and U.S.

Patent No. 5,428,149, entitled "Method for Palladium Catalyzed Carbon-Carbon

Coupling and Products" which are herein incorporated by reference. More specifically a

nucleobase includes, but is not limited to, uracil, cytosine, N4-protected cytosine, 4-

30   thiouracil, isocytosine, 5-methyluracil (thymine), 5-substituted uracils, adenine, N6-

protected adenine, guanine, N2-protected guanine, 2,6-diaminopurine, halogenated

purines as well as heterocycles meant to mimic the purine or pyrimidine ring, such as

imidazole.

A "diene" is defined as a molecule bearing two conjugated double bonds. The

35   diene may even be non-conjugated, if the geometry of the molecule is constrained so as

9

5   to facilitate a cycloaddition reaction (Cookson (1964) J. Chem. Soc. 5416). The atoms

forming these double bonds can be carbon or a heteroatom or any combination thereof.

A "dienophile" is defined as a molecule bearing an alkene group, or a double

bond between a carbon and a heteroatom, or a double bond between two heteroatoms.

The dienophile can be any group, including but not limited to, a substituted or

10   unsubstituted alkene, or a substituted or unsubstituted alkyne. Typically, the dienophile

is a substituted alkene of the formula C=C-Z or Z'-C=C-Z, wherein Z and Z' are electron

withdrawing groups independently selected from the group consisting of CHO, COR,

COOH, COCl, COaryl, CN, NO_2, aryl, CH_2OH, CH_2Cl, CH_2NH_2, CH_2CN, CH_2COOH,

halogen, or C=C. In certain cases the groups attached to the alkene unit can be electron

15   donating groups, including but not limited to phenyl rings, conjugated double bonds,

alkyl groups, OMe groups or other X-alkyl moieties wherein X is an electron donating

group (these type of dienophiles undergo cycloadditions that are known generally as

reverse electron demand cycloadditions). Other examples of dienophiles include

compounds having the formula, $R_2C=X$, wherein X is a heteroatom, selected from the

20   group consisting of oxygen, nitrogen, phosphorus and sulfur. For example, molecules

bearing a primary amino group, such as amino acids or a lysine containing peptide, can

be converted to efficient dienophiles by reaction with formaldehyde to yield their

corresponding iminium salts as illustrated below. The latter undergo Diels-Alder

cycloaddition with macromolecules bearing a diene group under mild conditions in

25   aqueous solvents.

A "1,3-dipole" is defined as a compound that contains a consecutive series of

three atoms, a-b-c, where atom a contains a sextet of electrons in its outer shell and atom

c contains an octet with at least one unshared pair of electrons in its outer shell. Because

30   molecules that have six electrons in the outer shell of an atom are typically unstable, the

a-b-c atom example is actually one canonical structure of a resonance hybrid, where at

least one structure can be drawn. 1,3-dipoles can be divided into two main groups:

10

5   1)   Systems in which one of the canonical forms has a double bond on the

sextet atom (atom a) and the other canonical form has a triple bond on that atom:

$$\overset{+}{\overline{\quad}a\!\!=\!\!b\!\!\overset{\cdot\cdot}{\underset{}{c}}\text{-}} \quad\longleftrightarrow\quad \overset{+}{\overline{\quad}a\!\!\equiv\!\!b\!\!\overset{\cdot\cdot}{\underset{}{c}}\text{-}}$$

2)   Systems where the dipolar canonical form has a single bond on the sextet

atom (atom a) and the other canonical form has a double bond on that atom:

$$\overset{+}{\overline{\quad}a\!\!\overset{\cdot\cdot}{\underset{}{b}}\!\!\overset{\cdot\cdot}{\underset{}{c}}\text{-}} \quad\longleftrightarrow\quad \overset{+}{\overline{\quad}a\!\!=\!\!b\!\!\overset{\cdot\cdot}{\underset{}{c}}\text{-}}$$

10

For a review of this reaction type see "Advanced Organic Chemistry" (March, J.,

ed.) 836-839 (1992) John Wiley & Sons, NY, and "Frontier Orbitals and Organic

Chemical Reactions" (I. Fleming) 148-161 (1976) John Wiley & Sons, Ltd. Typical

examples of 1,3-dipoles include, but are not limited to nitrile ylids, nitrile imines, nitrile

15   oxides, diazoalkanes, azides, azomethine ylids, azomethine imines, nitrones, carbonyl

ylids, carbonyl imines and carbonyl oxides.

A "1,3-dipolarophile" is defined in the same manner as a "dienophile" or "diene"

(as described above). The macromolecule can be attached to either (or both) the 1,3-

dipole or the 1,3-dipolarophile.

20   A "1,3-dipolar cycloaddition reaction" can be generally represented as follows:

or

An "Ene reaction" can be generally represented as follows:

The reaction partners in an Ene reaction are referred to as an "ene" and an

25   "enophile." An "enophile" is defined in the same manner as a "dienophile" (see the above

11

5 description for dienophile). An "ene" can be any unsaturated group, including but not limited to, a substituted or unsubstituted alkene, or a substituted or unsubstituted alkyne. Typically, the "ene" is a substituted alkene of the formula $X-C=CH-CH_2-$ or $X'-C=C-X-CXH-$, wherein X and X' are electron donating groups. The macromolecule can be attached to either (or both) the ene component or the enophile component.

10   "Bioconjugate" as defined herein refers to any macromolecule which has been derivatized with another molecular entity. "Bioconjugation" or "Conjugation" refers to the derivatization of a macromolecule with another molecular entity.

As used herein a "support" refers to glass, including but not limited to controlled pore glass (CPG), glass slides, glass fibers, glass disks, materials coated with glass,

15 silicon chips and wafers including, but not limited to metals and composites containing glass; polymers/resins, including but not limited to polystyrene (PS), polyethylene glycol (PEG), copolymers of PS and PEG, copolymers of polyacrylamide and PEG, copolymers containing maleimide or maleic anhydride, polyvinyl alcohol and non-immunogenic high molecular weight compounds; and large biomolecules, including but not limited to

20 polysaccharides, such as cellulose, proteins and nucleic acids. The support can be, but is not necessarily, a solid support.

As used herein "immobilization" refers to the attachment, via covalent bond, to a support. Immobilization includes a functionality on the support or a derivatized support.

The term "functionality" as used herein refers to functional groups, including but

25 not limited to alcohols, carboxylates, amines, sulfonic acids and halides, that allow the attachment of one component of the cycloaddition system (e.g. a diene or a dienophile).

As used herein "derivatized" refers to molecules and/or supports that have been functionalized with a moiety capable of undergoing a cycloaddition reaction. A molecule or support that bears a moiety capable of undergoing a cycloaddition reaction without

30 functionalization also falls within this definition. Examples of moieties capable of undergoing a cycloaddition reaction, include but are not limited to a diene, dienophile, 1,3-dipole, 1,3-dipolarophile, ene, enophile or other moiety capable of undergoing a cycloaddition reaction.

12

5   The term "molecule" includes, but is not limited to biomolecules, macromolecules, diagnostic detector molecules (DDM's) and other small molecules, particularly small molecules for use in combinatorial chemistry.

       As used herein a "biomolecules" include, but are not limited to nucleic acids, oligonucleotides, proteins, peptides and amino acids, polysaccharides and saccharides,
10   glycoproteins and glycopeptides (in general, glycoconjugates) alkaloids, lipids, hormones, drugs, prodrugs, antibodies and metabolites.

       The term "macromolecules" as used herein refers to the product of the coupling of two macromolecules via cycloaddition.

       "Diagnostic detector molecules" ("DDM's") include, but are not limited to
15   fluorescent, chemiluminescent, radioisotope and bioluminescent marker compounds; antibodies, biotin and metal chelates.

       As used herein "cycloaddition reaction" refers to any reaction that occurs between two reactants by a reorganization of valence electrons through an activated complex, which is usually a cyclic transition state. The orbitals involved in this class of reactions
20   are typically π-systems although certain σ-orbitals can also be involved. The number of electrons associated with this type of reaction are of two types; 4n+2 and 4n, where n = 0, 1, 2, 3, 4, etc. Typical examples of cycloaddition reactions include, but are not limited to [1+2]-cycloaddition, such as reaction between carbenes and olefins, [2+2]-cycloaddition, such as reaction between olefins or reaction between ketenes and olefins, [3+2]-
25   cycloaddition, such as 1,3-dipolar cycloaddition, [2+4]-cycloaddition, such as the Diels-Alder reaction and ene reaction, [4+6]-cycloaddition, and cheleotropic reactions. Types of reactants involved in cycloaddition reactions include, but are not limited to, olefins, including but not limited to alkenes, dienes etc with or without heteroatoms, alkynes, with and without heteroatoms, aromatic compounds, such as anthracene, 1,3-dipoles,
30   carbenes and carbene-precursors.

       The "derivatized oligonucleotides" of this invention are generally represented by the following formulas:

13

wherein

B is a nucleobase;

A and A' are 2'-sugar substituents;

W is independently selected from the group consisting of an oligonucleotide having between 1-1000 nucleobases, X or H; and

X is a diene, dienophile, 1,3-dipole, 1,3 dipolarophile, ene, enophile, alkene, alkyne or other moiety capable of undergoing a cycloaddition reaction, additionally when X is attached to nucleobase B it can be attached to a carbon atom, an exocyclic nitrogen or an exocyclic oxygen.

In a preferred embodiment of the invention:

A and A' are independently selected from the group consisting of H, ^{2}H, ^{3}H, Cl, F, OH, NHOR^1, NHOR^3, NHNHR^3, NHR^3, =NH, CHCN, CHCl$_2$, SH, SR$_3$, CFH$_2$, CF$_2$H, CR$^2_2$Br, -(OCH$_2$CH$_2$)$_n$OCH$_3$, OR^4 and imidazole (see United States Patent Application Serial No. 08/264,029, filed June 22, 1994, entitled "Novel Method of Preparation of 2' Modified Pyrimidines Intramolecular Nucleophilic Displacement," which is incorporated herein by reference);

14

R^1 is selected from the group consisting of H and an alcohol protecting group;

R^2 is selected from the group consisting of =O, =S, H, OH, CCl_3, CF_3, halide, optionally substituted C_1-C_{20} alkyl (including cyclic, straight chain, and branched), C_2-C_{20} alkenyl, C_6-C_{20} aryl, C1-C20 acyl, C_1-C_{20} benzoyl, OR_4 and esters;

R^3 is selected from the group consisting of R^2, R^4, CN, C(O)NH_2, C(S)NH_2, C(O)CF_3, SO_2R^4, amino acid, peptide and mixtures thereof;

R^4 is selected from the group consisting of an optionally substituted hydrocarbon (C_1-C_{20} alkyl, C_2-C_{20} alkenyl, C_2-C_{20} alkynyl), an optionally substituted heterocycle, t-butyldimethylsilyl ether, triisopropylsilyl ether, nucleoside, carbohydrate, fluorescent label and phosphate;

Most preferably A is selected from the group consisting of H, OH, NH_2, Cl, F, $NHOR^3$, OR^4, $OSiR^4_3$. (See United States Patent Application Serial No. 08/264,029, filed June 22, 1994, entitled "Novel Method of Preparation of 2' Modified Pyrimidines Intramolecular Nucleophilic Displacement," filed June 22, 1994); and

X includes, but is not limited to an alkyl or substituted alkyl group bearing a conjugated diene unit, an alkoxy or substituted alkoxy group bearing a conjugated diene unit, CH_2CH_2CH=$CHCH_2CH_2O$, maleimide substituted alkoxy groups, dienophile substituted alkoxy groups, an alkylamino group or substituted alkylamino group bearing a conjugated diene unit, maleimide substituted alkylamino groups or substituted alkylamino groups, an alkylamino group or substituted alkylamino group bearing a dienophile moiety, a nitrile ylid, nitrile imine, nitrile oxide, diazoalkane, azide, azomethine ylid, azomethine imine, nitrone, carbonyl ylid, carbonyl imine and carbonyl oxide.

The alkyl groups on all the above listed moieties can have between 1-50 carbons, preferably 1-30 carbons.

As used herein a "linking molecule" is a molecular entity that connects two or more molecular entities through covalent interactions. More specifically a linking molecule is a multifunctional molecule that can be used to derivatize a molecule or support with a diene, dienophile or other moiety capable of undergoing a cycloaddition reaction. The linking molecules of this invention are generally represented by the following formulas:

15

$$X^{\diagdown L \diagup} X \qquad L{-\!\!-}(X)_n$$

wherein

 X is as defined above;

 n is an integer from 1-20; and

 L is a linker which includes, but is not limited to, compounds of the following

general formula:

wherein

 m, n, o is equal to 0, 1, 2 and

 Y is selected from NH, O, NH(CO)O, NH(CS)O, NH(CO)NH, NH(CO), S-S-S-,

 Si(OR)$_3$ and SiR$_2$ wherein

 R is selected from alkyl, aryl, substituted alkyl or substituted aryl, each having

between 1-50 carbon atoms.

 Other obvious substitutions for the substituents described above are also included

within the scope of this invention, which is not limited to the specific, but rather the

generalized formula of reaction.

5   Cycloaddition reactions, particularly Diels-Alder reactions, are uniquely suited as

a general method for the immobilization of molecules, particularly biomolecules to a

support. The cycloaddition of a diene and a dienophile is highly chemoselective and only

a suitably electronically configured diene and dienophile pair will react. The reaction

proceeds under mild conditions in a reasonable time-frame. Biomolecules such as

10   nucleic acids, oligonucleotides, proteins, peptides, carbohydrates, polysaccharides,

glycoproteins, antibodies and lipids generally do not contain moieties that can undergo

such a cycloaddition reaction. Thus, by specific introduction of a diene and dienophile

reaction partner, biomolecule immobilization to a support becomes possible with

unprecedented specificity.

15   The high selectivity of a diene or dienophile for reaction with the corresponding

dienophile or diene, respectively, eliminates the need to protect functional groups during

the synthesis of biomolecules, such as oligonucleotides or peptides. This is a tremendous

practical advantage over other functional groups used for immobilization in biomolecular

synthesis, in which the limited selectivity of the protection chemistry often determines

20   the immobilization yields. Additionally, the diene and dienophiles are not susceptible to

the side-reactions typically encountered in known immobilization methods. Because they

do not undergo hydrolysis or solvolysis reactions, these reactions can be performed in

aqueous media at near stoichiometric concentrations and thus conserve precious reagent.

The lack of such side reactions allows immobilization of biomolecules in unprecedented

25   yields and purities. The Diels-Alder cycloaddition reaction is accelerated by aqueous

solvents and therefore, uniquely suited for the derivatization or immobilization of

hydrophilic biomolecules. Finally, this method is typically much less pH sensitive than

most known alternatives.

In one embodiment of the present invention the biomolecule is an oligonucleotide.

30   The solvent of choice for the derivatization of oligonucleotides is water, due to the highly

anionic nature of these molecules. Thus, an optimal reaction for the immobilization of

such groups proceeds readily in water, and displays no side reactions with water, such as

hydrolysis of any of the reactants. Based on these criteria for optimal and specific

immobilization of oligonucleotides, this disclosure describes the use of Diels-Alder

35   cycloadditions for the chemoselective and efficient immobilization oligonucleotides on a

17

5   support. Thus, an oligonucleotide bearing either a diene modified nucleoside or non-
nucleoside phosphate diester group, or a dienophile modified nucleoside or non-
nucleoside phosphate diester group can be reacted with a support bearing either a
dienophile or a diene moiety, respectively.

The diene or dienophile moiety can be incorporated into the oligonucleotide at

10   any position in the chain, for instance, by introduction of a 5-(3,5-hexadiene)-2'-
deoxyuridine nucleoside (See U.S. Patent Application Serial No. 08/264,029, filed June
22, 1994, entitled "Novel Method of Preparation of Known and Novel 2'-modified
Nucleosides by Intramolecular Nucleophilic Displacement," which is incorporated herein
by reference in its entirety). Alternatively, the diene or dienophile moiety can be

15   introduced as a 2'-O-(3,5-hexadiene)-uridine nucleoside. A diene moiety can also be
introduced to the oligonucleotide as a diene-bearing non-nucleoside phosphoramidite,
such as 3,5-hexadiene-N,N-diisopropyl-2-cyanoethyl phosphoramidite. Reaction of the
diene modified oligonucleotide, such as a 5'-terminal 3,5-hexadienephosphate
oligonucleotide, with the dienophile modified support, such as maleimide derivatized

20   glass, leads to efficient immobilization of the oligonucleotide.

The method of this invention can be extended to the immobilization of any
molecule that can be derivatized with a diene, dienophile or other reactive group capable
of undergoing a cycloaddition reaction without limitation. For example, the method can
be extended to the immobilization of peptides and proteins with any support capable or

25   being derivatized. A peptide or protein that contains an amino acid building block which
has been derivatized with the diene or dienophile, such as O-3.5-hexadiene-tyrosine or
serine, or N-maleimidolysine, can be immobilized on any support using the method
described herein, without limitation. Natural molecules, such as proteins, can be
derivatized with a diene or dienophile bearing a heterobifunctional crosslinking reagent,

30   such as the NHS ester of 3-(4-maleimidophenyl)-propionic acid (Pierce), which allows
subsequent conjugation to a support bearing a corresponding diene or dienophile group.

Polyethylene glycol is often conjugated to biomolecules to reduce their
immunogenicity and to increase their residence time *in vitro*. The method of this
invention allows immobilization of biomolecules, such as oligonucleotides or peptides,

35   bearing a diene, dienophile or other reactive group capable of undergoing a cycloaddition

18

5   reaction with another polymer or resin, such as polyethyleneglycol or polystyrene bearing

one or several corresponding diene, dienophile or other groups capable of undergoing

cycloaddition reactions.

Example 1 (Scheme 1) describes the synthesis of 5-hydroxymethylcyclohexa-1,3-

diene (5).

10   Example 2 (Scheme 2) describes the preparation of NHS reagent (10) from

cyclohexadiene alcohol (5).

Example 3 (Scheme 3) describes the synthesis of the diene amidite linker (16)

from amino-linker (12). Amino-linker (12) was developed in mimesis of a nucleoside

containing a primary (as 5'-OH) and a secondary hydroxyl group (as 3'-OH). This allows

15   the conjugation of the linker on either the 3'- or 5'-end of any oligonucleotide. The

attachment of various moieties to the oligonucleotide (e.g., dienes or dyes) is achieved

via the linker's amino functionality. Therefore, compound (12) is recognized as a

universal linker for conjugation of oligonucleotides.

Example 4 (Scheme 4) describes the synthesis of maleimide-trialkoxy silane (19),

20   which is used to functionalize glass surfaces.

Example 5 describes the synthesis of diene-trialkoxy silane (20) for the

functionalization of glass surfaces.

Example 6 describes the synthesis of three 5' functionalized oligonucleotides,

compounds (23), (24) and (26). Compounds (23) and (23) (Scheme 6) are functionalized

25   at the 5' end with a diene by reaction with diene-linker amidite (16). Compound (26)

(Scheme 7) is functionalized at the 5' end with a maleimide by reaction with

maleimidopropionic acid N-hydroxysuccimide ester (compound 18, Scheme 4).

Examples 7 and 8 describe a method for the functionalization of two glass

surfaces, specifically glass slides and CPG, with both a diene and a dienophile. Glass

30   surfaces are derivatized with reactive moieties capable of undergoing cycloaddition

reactions by deposition of silane monolayers appropriately functionalized for

cycloaddition reaction. Specifically, Example 7 describes the functionalization of the

two glass surfaces with maleimide dienophile (19) (Scheme 8). Example 7 also describes

methods for the detection of the maleimide functionalized surfaces. The maleimide

35   derivatized surfaces are detected by staining with a thiol-fluorescein reagent, which reacts

19

with the maleimide via a Michael-addition as illustrated in Scheme 9. The presence of fluorescein bound to the surfaces is then detected with a Molecular Dynamics' Tyhpoon Fluorescence Scanner using a green laser to excite the surface-bound fluorescein followed by detection of emission using a 526 nm filter.

Example 8 describes the functionalization of the two glass surfaces with diene (20) (Scheme 10). Example 8 also describes methods for the detection of the functionalized surfaces. The diene derivatized surfaces are detected by Diels-Alder reaction with a fluorescein maleimide as illustrated in Scheme 11.

Example 9 (Scheme 12) describes the Diels-Alder reaction between the 5' diene functionalized oligonucleotide (23) and maleimide functionalized glass slides and microtiter plates. This reaction demonstrates the Diels-Alder surface immobilization of an oligonucleotide (Scheme 12). Detection of the surface-bound oligonucleotide was achieved by its hybridization to a fluorescein-labeled complementary sequence (27) and detection of fluorescence. The results of this Example are set forth in Figure 8.

Example 10 describes the Diels-Alder reaction between maleimide-CPG and diene derivatized oligonucleotide (24). In Example 9, the conjugation of the diene-oligonucleotide to the maleimide derivatized support was detected by the fluorescence of a labeled complementary sequence after hybridization. This method of detection, however, gives a qualitative result, but does not allow the quantitative determination of surface loading. In Example 10, a different detection method was selected for determination of immobilized oligonucleotide in order to obtain a quantitative determination of surface loading. For purposes of illustration, diene(DMT)-oligonucleotide (24) was used. After Diels-Alder reaction between diene (24) and maleimide, the surface bound amount of oligonucleotide (loading) is calculated after the cleavage of the DMT-group by photometric detection of the DMT-cation as illustrated in Scheme 12.

Maleimide-derivatized CPG was incubated with increasing amounts of oligonucleotide (24) in order to demonstrate the relation between oligonucleotide immobilization (as CPG loading) and the amount of diene-oligonucleotide in solution. Using this method the typical range of oligonucleotide loading was calculated to be 0.8-1.7 µmol/g (Table 2, Figure 9). The results obtained from this experiment also showed

20

5   that not all maleimide-sites were reacted with diene-oligonucleotide and that the loading

can be further increased be treatment with larger amounts of (24) by achieving an

exponential dependence instead of a linear curve fit.

The kinetic relationship between loading and incubation time was also

demonstrated. As expected an exponential curve was obtained, but the plateau of the

10   curve was not reached in the time-frame applied for the experiment (Table 3, Figure 10).

After approximately 100 minutes a saturation (by consumption of all oligonucleotide (24)

in solution) was achieved. The most interesting result shows that even after an

incubation time of 5 minutes, a loading of 0.4 μmol/g was obtained. Compared with the

data from the first example, the concentration of 17 applied in this example is too low to

15   saturate all of the maleimide sites of the CPG support.

Example 11 (Scheme 14) describes the conjugation of 5'-maleimide derivatized

oligonucleotide (26) to diene coated glass surfaces. The demonstration of conjugation

was achieved by hybridization with the labeled complementary sequence (27) and the

detection of fluorescence as described above.

20   Example 12 (Scheme 15) describes the synthesis of diene modified

oligonucleotide (29) from NHS reagent (10), the synthesis of which is described in

Example 2.

Example 13 (Scheme 16) describes the HPLC monitoring of a Diels-Alder

reaction employing a cyclohexadiene derivatized oligonucleotide. To confirm the Diels-

25   Alder reactivity of diene conjugate (29), labeling with commercially available maleimide

dienophiles (30) and (31) were carried out. The progress of the reaction was monitored

by analytical anion exchange chromatography with samples taken every 5 minutes.

Treatment of (29) with N-ethyl maleimide (30) resulted in complete conversion to adduct

(32) within 5 minutes, while biotin maleimide 31 required 20 minutes.

30   Example 14 (Scheme 17) describes the synthesis of diene modified polyethylene

glycol substrates (34). Example 14 (Scheme 18) also describes the synthesis of

anthracene derivative (36).

Example 15 (Scheme 19) describes the preparation of a dienophile CM5 BIAcore

flow cell surface.

21

Example 16 (Scheme 20) describes a comparison of surface derivatization via

PEG-SH (Michael-addition) vs PEG-diene (Diels-Alder surface immobilization).

Example 17 (Scheme 21) describes the Diels-Alder reaction of dienophile

derivatized CM5 BIAcore flow cell surface (37) with anthracene derivative (36)

(preparation described in Example 14), using the method described in Example 16 to

10   provide compound (38).

Example 18 (Scheme 22) describes the surface immobilization of the

cyclohexadiene modified oligonucleotide (29) to the dienophile derivatized CM5

BIAcore flow cell surface (37), followed by hybridization with the complementary

oligonucleotide sequence.

15   Example 19 (Scheme 23) describes the synthesis of anthracene-silane reagent

(42).

Example 20 (Scheme 24) illustrates the functionalization of glass slides with

anthracene-silane reagent (42).

The following examples are provided to explain and illustrate the present

20   invention and are not to be taken as limiting of the invention.

EXAMPLES

Example 1. Preparation of Cyclic Diene Alcohol (5)

Scheme 1 illustrates the preparation of cyclohexadiene (5). Briefly, the synthesis

25   of diene-alcohol (5) was obtained from alcohol (1) in four steps by a scaleable and very

convenient procedure as outlined in Scheme 1. This diene has been synthesized via a

different route by Roth et al. ((1993) Chem. Ber. 126:2701-2715).

Scheme 1

Synthesis of 4-(*tert*-butyldimethylsilyloxymethyl)-cyclohex-1-ene (2). To a stirred
solution of 1,2,3,6-tetrahydrobenzylalcohol (1) (1.12 g, 10 mmol) and imidazole (1.36 g,
20 mmol) in DMF (10 mL) was added TBDMSCl (1.81 g, 12 mmol). After 20 hours, the
mixture was treated with brine (100 mL) and the product was extracted with hexanes
(3x80 mL). The combined organic layers were washed with brine (100 mL), dried over
MgSO$_4$ and evaporated *in vacuo* to give compound (2) (2.26 g, 100%) as colorless liquid.
R_f 0.29 (hexanes). ^{1}H NMR (CDCl$_3$) δ 5.65 - 5.64 (m, 2H), 3.48 (d, J = 2.3 Hz, 1H), 3.45
(d, J = 2.3 Hz, 1H), 2.08 - 2.00 (m, 3H), 1.82 - 1.66 (m, 3H), 1.32 - 1.19 (m, 1H), 0.89 (s,
9H), 0.04 (s, 6H); ^{13}C NMR (CDCl$_3$) δ 127.04, 126.23, 67.95, 36.34, 28.23, 25.97, 25.70,
25.33, 24.78, 18.38, -5.32.

Synthesis of trans-1,2-dibromo-3-(tert-butyldimethylsilyloxymethyl)-cyclohexane (3).
To a stirred solution of alkene (2) (1.81 g, 8 mmol) in CCl$_4$ (15 mL) was added bromine
(0.4 mL, 8 mmol) in CCl$_4$ (1 mL) dropwise. The resulting red mixture was diluted with
CH$_2$Cl$_2$ (50 mL) and washed with 10% Na$_2$S$_2$O$_3$ solution (50 mL) and water (50 mL).
The organic phase was dried over Na$_2$SO$_4$ and evaporated *in vacuo* to give 2.98 g (96%)
of compound (3) as a yellow oil. R_f 0.20 (100:1 hexane/EtOAc). ^{1}H NMR (CDCl$_3$) δ
4.71 - 4.64 (m, 2H), 3.47 (d, J = 5.3 Hz, 2H), 2.52 - 2.40 (m, 2H), 2.23 - 1.52 (m, 5H),
0.89 (s, 9H), 0.04 (s, 6H). ^{13}C NMR (CDCl$_3$) δ 67.27, 53.60, 53.45, 34.23, 31.41, 28.12,
25.88, 23.25, 18.26, -5.39.

Synthesis of 5-hydroxymethylcyclohexa-1,3-diene (5). To stirred 0 °C solution of
dibromide (3) (69.52 g, 0.18 mol) and Aliquat 336 (1.46 g, 3.6 mmol, 0.02 equiv) in THF
(500 mL) was added KOtBu (44.89 g, 0.4 mol, 2.2 equiv). Immediate formation of a
yellow precipitate occurred and after 5 minutes the cooling bath was removed. After 30
minutes, an aliquot of the mixture was removed and dried under a stream of argon. ^{1}H
NMR analysis (C$_6$D$_6$) indicated that only a trace of dibromide (3) was remaining. After
an additional 40 minutes, the mixture was evaporated *in vacuo*, diluted with hexane (300
mL) and washed with a saturated NH$_4$Cl solution (300 mL). After separation the aqueous
layer was extracted with hexane (200 mL) and the combined organic layers were washed
with water (300 mL), dried over MgSO$_4$ and evaporated *in vacuo* to afford 65 g of crude

23

5   diene (4). This material was dissolved in MeOH (600 mL) and treated with Dowex

50WX4-50 (65 g). The slurry was shaken at 200 rpm for 140 minutes after which time

TLC indicated no remaining (4). The resin was filtered and washed with MeOH. The

filtrate was evaporated *in vacuo* and the resulting residue was distilled bulb-to-bulb under

reduced pressure to give diene (5) (16.71 g, 84%) as a colorless liquid. Bp 47 °C (2.2

10   mbar) – 50 °C (1.7 mbar); R_f 0.49 (1:1 hexane/EtOAc). ^{1}H NMR (CDCl$_3$) δ 5.98 - 5.62

(m, 4 H), 3.58 (d, J = 5.9 Hz, 2 H), 2.56 - 2.42 (m, 1 H), 2.37 - 2.05 (m, 2 H), 1.50 (s, 1

H). ^{13}C NMR (CDCl$_3$) δ 126.92, 125.39, 124.98, 123.63, 64.58, 35.47, 24.91.

Example 2. Preparation of NHS reagent (10)

15   Scheme 2 illustrates the preparation of NHS reagent (10) from diene (5).

Scheme 2

24

5   Synthesis of 13-*N*-(5-cyclohexa-1,3-dienemethoxycarbonyl)-4,7,10-trioxa-1,13-
     tridecanediamine (8). To a stirred solution of diene (5) (1.10 g, 10 mmol) in THF (20
     mL) was added 1,1'-carbonyldiimidazole (CDI) (1.63 g, 10.05 mmol). After 40 minutes,
     a solution of 4,7,10-trioxa-1,13-tridecanediamine (7) (4.4 mL, 20 mmol) in THF (5 mL)
     was added. After 50 minutes the reaction mixture was diluted with EtOAc (50 mL) and
10   washed with brine (50 mL) and water (2x50 mL). The organic phases were combined,
     dried over $MgSO_4$ and evaporated *in vacuo*. Purification via chromatography on the
     Biotage Flash 40 system eluting with CH_2Cl_2/MeOH/Et_3N (15:1:0.1) afforded 2.62 g
     (74%) of carbamate (8) as a colorless oil. R_f 0.48 (5:3:1 $CHCl_3$/MeOH/AcOH, 32%). ^{1}H
     NMR ($CDCl_3$) δ 5.94 - 5.82 (m 2 H), 5.74 - 5.69 (m, 1 H), 5.64 - 5.59 (m, 1 H), 5.50 (s, 1
15   H), 3.96 (d, J = 7.0 Hz), 3.63 - 3.49 (m, 12 H), 3.25 (q, J = 6.5, 5.9 Hz, 2 H), 2.76 (t, J =
     6.7 Hz, 2 H), 2.61 - 2.49 (m, 1 H), 2.28- 2.18 (m, 1 H), 2.13 - 2.03 (m, 1 H), 1.78 - 1.65
     (m, 4 H); ^{13}C NMR ($CDCl_3$) δ 156.20, 125.94, 124.68, 123.28, 69.90, 69.50, 68.79,
     68.65, 65.25, 38.94 38.05, 32.50, 32.32, 28.90, 24.55.

20   Synthesis of 18-*N*-(5-cyclohexa-1,3-dienemethoxycarbonyl)-18-amino-5-aza-4-keto-
     9,12,15-trioxa-18-octadecanoic acid (9). To a solution of amine (8) (1.43 g, 4 mmol) and
     N-methylimidazole (NMI) (0.64 mL, 8 mmol) in pyridine (20 mL) was added succinic
     anhydride (0.44 g, 4.4 mmol). This mixture was stirred for 2 hours, evaporated *in vacuo*
     and the residue was purified by silica gel chromatography on the Biotage Flash 40 system
25   eluting with CH_2Cl_2/MeOH/Et_3N (10:1:0.1). To remove Et_3N, the product was dissolved
     in MeOH (20 mL) and treated with Dowex MWC-1 (2 g) for 1 hour. The solids were
     filtered and the filtrate was evaporated *in vacuo* to yield 1.50 g (82%) of acid (9) as
     slightly yellow oil. R_f 0.64 (5:3:1 $CHCl_3$/MeOH/AcOH, 32%), 0.12 (10:1:0.1
     $CHCl_3$/MeOH/Et_3N). ^{1}H NMR ($CDCl_3$) δ 7.15 - 6.98 (m, 1 H), 5.97 - 5.82 (m, 2 H), 5.77
30   - 5.69 (m, 1 H), 5.65 - 5.60 (m, 1 H), 5.37 - 5.28 (m, 1 H), 3.98 (d, J = 7.0 Hz, 2 H), 3.64
     - 3.46 (m, 12 H), 3.31 (q, J = 6.5, 5.9 Hz), 3.26 (q, J = 6.5, 5.9 Hz), 2.61 - 2.51 (m, 3 H),
     2.46 (t, J = 6.2 Hz, 2 H), 2.33 - 2.20 (m, 1H), 2.18 - 2.02 (m, 1 H), 1.79 - 1.71 (m, 4 H).
     ^{13}C NMR ($CDCl_3$) δ 175.46, 172.40, 156.69, 126.32, 125.21, 123.79, 70.29, 70.24, 69.86,
   69.65, 69.23, 66.01, 38.71 37.80, 32.74, 30.89, 30.12, 29.32, 28.61, 25.02.

35

Synthesis of 18-N-(5-cyclohexa-1,3-dienemethoxycarbonyl)-18-amino-5-aza-4-keto-9,12,15-trioxa-18-octadecanoic acid N-hydroxysuccinimide ester (10). To a stirred 0 °C solution of acid (9) (913 mg, 2 mmol), N-hydroxysuccinimide (230 mg, 2 mmol) and DMAP (12 mg, 0.1 mmol) in CH_2Cl_2 (10 mL) was added dicyclohexylcarbodiimide (433 mg, 2.1 mmol). After 5 minutes the cooling bath was removed. After 2 hours, TLC indicated incomplete conversion and additional N-hydroxysuccinimide (46 mg, 0.4 mmol) and dicyclohexylcarbodiimide (83 mg, 0.4 mmol) were added. After 22 hours, TLC analysis still indicated incomplete conversion and more N-hydroxysuccinimide (46 mg, 0.4 mmol) and dicyclohexylcarbodiimide (83 mg, 0.4 mmol) were added. After 3 hours, the mixture was filtered through Celite and the precipitate was washed with CH_2Cl_2 (10 mL). The filtrate was evaporated *in vacuo* and the residue was dissolved in EtOAc (5 mL), again filtered and evaporated *in vacuo*. Flash chromatographic purification employing the Biotage Flash 40 system eluting with a gradient of hexane/acetone 1:1 → 1:0.8 → 1:0.6 afforded 370 mg (33%) of NHS-ester (10) as a colorless oil. R_f 0.45 (10:1:0.2 $CHCl_3$/MeOH/AcOH), 0.32 (1:2 hexane/acetone). ^1H NMR ($CDCl_3$) δ 6.69, 6.52 (2s 1 H), 5.91 - 5.82 (m, 2 H), 5.73 - 5.69 (m, 1 H), 5.63 - 5.59 (m, 1 H), 5.25 (s, 1 H), 3.95 (d, J = 6.5 Hz, 1 H), 3.60 - 3.48 (m, 12 H), 3.34 - 3.30 (m, 2 H), 3.23 - 3.20 (m, 1 H), 2.97 - 2.90 (m, 2 H), 2.79 (s, 4 H), 2.73 - 2.50 (m, 3 H), 2.32 - 2.02 (m, 2 H), 1.75 - 1.71 (m, 4 H). ^{13}C NMR ($CDCl_3$) δ 169.63, 168.94, 168.08, 156.47, 126.31, 125.16, 125.11, 123.70, 70.23, 70.20, 69.70, 69.77, 69.22, 65.85, 38.73, 37.92, 32.70, 30.25, 29.26, 28.53, 26.54, 25.36, 24.94.

Example 3. Synthesis of Diene Phosphoramidite (16)

The synthesis of the diene-phosphoramidite (16), which is suitable for the attachment to the 5'-end of an oligonucleotide, is outlined in Scheme 3. Briefly, starting from the commercially available and enantiomerically pure alcohol (11) the universal linker (12) was obtained by $LiAlH_4$ reduction. The crude amine was acylated with diene-carbamate (6), generated *in situ* by the reaction of diene (5) with carbonydiimidazole (CDI) as described in Example 1. The crude product, diol (13) was then acetylated to enable purification by flash-chromatography. After purification, the acetates were cleaved and the crude diol was selectively tritylated with 4,4'-dimethoxytrityl chloride

5   (DMT) to give the alcohol (15). Alcohol (15) was then reacted with 2-cyanoethyl-bis-

(N,N-diisopropylamino)-phosphoramidite and 4,5-dicyanoimidazole (DCI) to produce

amidite (16), which was then purified by flash-chromatography.

Scheme 3

a: $NC(CH_2)_2OP(NiPr_2)_2/DCI$, CH_2Cl_2

10 Synthesis of (S)-5-amino-pentane-1,3-diol (12). $LiAlH_4$ (26.5 g, 0.70 mol) was

suspended in anhydrous THF (250 mL) and cooled to 0 °C. Alcohol (11) (20.0 g, 0.13

mol), dissolved in anhydrous THF (100 mL), was added dropwise. The mixture was

warmed to room temperature and stirred overnight. After cooling to 0 °C, the mixture

was treated sequentially with H_2O (12.6 mL, 0.70 mol), 10 N NaOH (34.9 mL, 0.35 mol)

15 and H_2O (37.8 mL, 2.10 mol). The resulting solids were removed by filtration and the

filtrate was concentrated *in vacuo*. The material recovered (12.7 g, 84%) was consistent

with the desired amine-diol (12).

Synthesis of (S)-O-cyclohexa-2,4-dienylmethyl-N-(3,5-diacetoxypentyl)-carbamate (14).

20 Diene-carbamate (6) was generated *in situ* by addition of CDI (3.5 g, 21.6 mmol) to a

solution of diene-alcohol (5) (2.0 g, 18.2 mmol) in DMF (17 mL). After stirring for 2

hours the crude amine (12) (2.0 g, 16.8 mmol) was added and stirring was continued

overnight. The mixture was concentrated *in vacuo* and the residue dissolved in CH_2Cl_2

27

5   (55 mL). After addition of Et$_3$N (23.4 mL, 168 mmol), the mixture was cooled to 0 °C

and treated with Ac$_2$O (15.9 mL, 168 mmol). The solution was allowed to warm to room

temperature and stirring was continued overnight. The reaction mixture was washed with

a saturated NaHCO$_3$ solution (50 mL) and brine (50 mL), dried over Mg$_2$SO$_4$ and

concentrated *in vacuo*. The crude product was then purified by flash chromatography

10   (Biotage Flash 40 system) on silica gel, eluting with EtOAc/CH$_2$Cl$_2$ (1:4 v/v) to yield 1.9

g (33%) of carbamate (14) as a colorless oil: R_f 0.24 (EtOAc/CH$_2$Cl$_2$ 1:4 v/v). ^{1}H NMR

(300 MHz, CDCl$_3$) δ 5.97-5.62 (m, 4H), 5.10-5.00 (m, 2H), 4.12-3.97 (m, 4H), 3.40-3.34

(m, 2H), 3.02-2.94 (m, 2H), 2.67-2.58 (m, 2H), 2.67-2.58 (m, 1H), 2.30-1.64 (m, 8H).

ES-MS (pos): [M + H]$^+$ 340 (339.2 calcd).

15

Synthesis of (S)-O-cyclohexa-2,4-dienylmethyl-N-[5-(4,4'-dimethoxytrityl)-3-

hydroxypentyl]-carbamate (15). Diacetate (14) (1.9 g, 5.6 mmol) was dissolved in

MeOH (30 mL) and K$_2$CO$_3$ (39 mg, 0.3 mmol) was added. After 2 hours, the mixture

was concentrated *in vacuo* and the residue was dried by azeotropic distillation with

20   pyridine (2x20 mL). The crude diol was dissolved in pyridine (37 mL) and treated with

4,4'-dimethoxytrityl chloride (3.77 g, 11.1 mmol). The reaction was stirred overnight and

then concentrated to a residue. The reddish oil was dissolved in EtOAc (50 mL) and

washed sequentially with a saturated NaHCO$_3$ solution (50 mL) and brine (50 mL). The

organic phase was dried over MgSO$_4$, filtered and concentrated *in vacuo*. The crude

25   residue was purified by flash chromatography (Biotage Flash 40 system) on silica gel,

eluting with EtOAc/CH$_2$Cl$_2$ (1:9 v/v) to yield 1.0 g (32%) of alcohol (15) as a slightly

yellow oil. R_f 0.21 (EtOAc/CH$_2$Cl$_2$ 1:9 v/v). ^{1}H NMR (300 MHz, CDCl$_3$) δ 7.42-7.15

(m, 8H), 6.85-6.82 (m, 4H), 5.97-5.85 (m, 2H), 5.77-5.62 (m, 2H), 5.20 (m, 1H), 4.04-

3.99 (m, 2H), 3.86-3.80 (m, 8H), 3.51-3.35 (m, 3H), 3.19-2.26 (m, 2H), 2.63 (m, 1H),

30   2.26-2.04 (m, 2H), 1.85-1.53 (m, 4H).

Synthesis of (S)-O-cyclohexa-2,4-dienylmethyl-N-{3-[(2-cyanoethoxy)-

diisopropylaminophosphano]-5-(4,4'-dimethoxytrityl)}-3-hydroxypentyl]-carbamate (16).

A solution of alcohol (15) (1.00 g, 1.8 mmol) in anhydrous CH$_2$Cl$_2$ (18 mL) was treated

35   with 2-cyanoethyl-bis-(N,N-diisopropylamino)-phosphoramidite (0.60 g, 2.0 mmol),

28

5   followed by 4,5-dicyanoimidazole (0.11 g, 0.9 mmol). After stirring for 1 hour, TLC

analysis indicated complete conversion of (15). The mixture was diluted with CH_2Cl_2

(30 mL), washed with a saturated $NaHCO_3$ solution (30 mL) and brine (30 mL), dried

over Mg_2SO_4 and concentrated *in vacuo*. The crude residue was purified by flash

chromatography (Biotage Flash 40 system) on silica gel, eluting with $EtOAc/CH_2Cl_2$ (1:9

10   v/v) to afford 933 mg (68%) of amidite (16) as a colorless foam. R_f 0.40 ($EtOAc/CH_2Cl_2$

1:9 v/v). ^1H NMR (300 MHz, $CDCl_3$) δ 7.43-7.17 (m, 8H), 6.84-6.79 (m, 4H), 5.97-5.85

(m, 2H), 5.77-5.62 (m, 2H), 5.48 (m, 1H), 4.06-3.97 (m, 3H), 3.85-3.45 (m, 10H), 3.30-

3.12 (m, 4H), 2.68-2.61 (m, 3H), 2.46-2.42 (m, 1H), 2.23-1.59 (m, 8H), 1.16-1.02 (m,

12H). ^{31}P NMR (121 MHz, $CDCl_3$) 149.08, 148.38. ES-MS (pos): $[M+H_3O]^+$ 776

15   (776.4 calcd).

Example 4. Synthesis of a Maleimide-Silane Reagent

Scheme 4 illustrates the synthesis of a maleimide-silane reagent for the

functionalization of glass surfaces. Briefly, with reference to Scheme 4,

20   propylaminosilane (17) was reacted with the functionalized maleimide N-

hydroxysuccinimide-ester (18), to provide after aqueous work-up maleimide-silane (19),

which was used as a crude product for derivatization of glass surfaces.

Scheme 4

17   18   19

25

Synthesis of 3-maleimido-N-(3-triethoxysilanylpropyl)-propionamide (19). 3-

Maleimidopropionic acid N-hydroxysuccinimide ester (18) (4.0 g, 15.03 mmol, 1.0

equiv.) was dissolved in N,N-dimethylformamide (75 mL) and 3-

aminopropyltriethoxysilane (17) (5.06 mL, 15.03 mmol, 1 equiv.) was added and the

30   reaction mixture was allowed to stir for 22 hours. An aliquot (0.15 mL) was removed by

syringe, concentrated *in vacuo*, and the resulting oil was analyzed by ^1H NMR

spectroscopy. The oil was consistent with desired product. The reaction mixture was

then concentrated *in vacuo* at 50-55 °C and the residue obtained was dissolved in CH_2Cl_2

29

5   (75 mL), washed with water (3x50 mL) and brine (50 mL), filtered through granular

Na_2SO_4, and concentrated under reduced pressure *in vacuo* to provide 6.65 g (>100% due

to residual N,N-dimethylformamide) of the crude maleimide-silane (19) as a light yellow

oil. Crude (19) was used without purification. ^1H NMR (300 MHz, $CDCl_3$) δ 6.65 (s,

2H), 6.00 (s, 1H), 3.77 (q, *J* = 7 Hz, 6H), 3.70 (m, 2H), 3.17 (m, 2H), 2.46 (m, 2H), 1.56

10   (m, 2H), 1.18 (t, *J* = 7 Hz, 9H), 0.57 (m, 2H). ^{13}C NMR (75 MHz, $CDCl_3$) δ 170.36,

169.28, 134.09, 58.35, 41.77, 34.56, 34.21, 23.20, 18.20, 7.65. FB-MS (pos): $[M+H]^+$

373 (373.2 calcd).

Example 5. Synthesis of a Diene-Silane Reagent

15   Scheme 5 illustrates the synthesis of a diene-silane reagent for the

functionalization of glass surfaces. Briefly, with reference to Scheme 5, analogous to the

synthesis of linker (13), diene (5) was treated with carbonyldiimidazole. To the

imidazolate formed *in situ* was added amine (17). After stirring overnight the product of

the reaction mixture, diene-silane (20) was separated and used as a crude product for

20   glass surface functionalizations.

Scheme 5

17   5   20

Synthesis of O-cyclohexa-2,4-dienylmethyl-N-(3-triethoxysilanylpropyl)-carbamate (20).
Diene alcohol (5) (0.50 g, 4.54 mmol, 1.0 equiv.) was dissolved in N,N-

25   dimethylformamide (15 mL), carbonyldiimidazole (0.77 g, 4.77 mmol, 1.05 equiv.) was

added and the mixture was allowed to stir for 4 hours. The formation of the imidazolate

intermediate (6) (Scheme 2) was confirmed by ^1H NMR spectroscopic analysis of an

aliquot (0.3 mL) of the reaction mixture that was concentrated *in vacuo* to an oil. The oil

was consistent with desired intermediate by ^1H NMR spectroscopy as evidenced by the

30   chemical shift in the resonance of the methylene protons from 3.6 ppm to 4.3 ppm. 3-

Aminopropyltriethoxy silane (17) (1.51 mL, 4.50 mmol, 1.0 equiv.) was then added and

the reaction mixture was stirred for 12 hours. The formation of the desired product (20)

was confirmed by ^1H NMR spectroscopic analysis of an aliquot (0.3 mL) of the reaction

5   mixture that was concentrated *in vacuo* to an oil. The oil was consistent with desired product as evidenced by the chemical shift in the resonance of the methylene protons from 4.3 ppm to 4.0 ppm. The reaction mixture was concentrated at reduced pressure, *in vacuo* overnight and imidazole crystallized out of the resulting brown oil. The oil obtained was separated from the crystals by pipette and transferred to a clean round-

10   bottom flask to provide 1.5 g (93%) of the desired diene-silane (20) as a brown oil. Crude (20) was used without further purification. ^{1}H NMR (300 MHz, CDCl$_3$) δ 5.98 – 5.63 (m, 4H), 4.95 (s, 1H), 4.00 (m, 2H), 3.82 (q, J = 7 Hz, 6H), 3.16 (m, 2H), 2.62 (m, 1H), 2.16 (m, 2H), 1.62 (m, 2H), 1.23 (t, J = 7 Hz, 9H), 0.64 (m, 2H). ^{13}C NMR (75 MHz, CDCl$_3$) δ 158.67, 135.41, 126.70, 125.59, 124.14, 66.39, 58.66, 43.16, 33.15,

15   25.42, 23.85, 18.52, 7.81. FB-MS (pos): [M+H]$^+$ 358 (358.2 calcd).

Example 6. Synthesis of Labeled Oligonucleotides

       The synthesis of various labeled and unlabeled (for control experiments) oligonucleotides is illustrated in Schemes 6 and 7 below. All syntheses were carried out

20   employing standard procedures for solid phase oligonucleotide synthesis using phosphoramidite building blocks and a CPG solid support. The 20 mer (22) (SEQ ID NO:1) was chosen for purposes of illustration. With reference to Scheme 6, DNA oligonucleotide (22) was synthesized on CPG performing the standard protocol to give the CPG bound oligonucleotide (21). An aliquot of (21) was deprotected and cleaved

25   from the CPG support, to provide the crude control oligonucleotide (22). The diene labeled oligonucleotide (23) was synthesized by prolongation of the 5'-end of (21) with the diene-linker amidite (16). After further processing and detritylation/cleavage the crude oligonucleotide was subjected to AX-HPLC to yield 86% of pure (23).

       In a second experiment, the diene-functionalized CPG bound oligonucleotide

30   obtained from step c was divided into two portions. One portion was cleaved and deprotected without detritylation to give crude diene(DMT)-oligonucleotide (24) (Scheme 6) and the second portion was processed as described above, but without purification to give crude diene-oligonucleotide (23).

35

31

Scheme 6

3'-GTG TGT GTG TGT GTG TGT GT-5' (SEQ ID NO:1)

22

24

Key: a: coupling; b: oxidation; c: capping; d: detritylation;
e: deprotection and cleavage from CPG; f: purification

In order to perform the Diels-Alder cycloaddition in the reverse direction a
maleimide functionalized oligonucleotide was synthesized as illustrated in Scheme 7.

10   With reference to Scheme 7, the standard sequence was synthesized on a CPG support
and extended with a protected amino-linker. Following deprotection and cleavage from
the CPG support the 5'-aminohexyloligonucleotide product (25) was acylated with the
maleimide NHS-ester (18). Following filtration through Sephadex the crude maleimide-
oligonucleotide (26) was obtained.

15   In order to allow fluorescence detection of the immobilized oligonucleotide by
hybridization with a dye-labeled complementary sequence the 20 mer 5'-fluorescein-
CACACACACACACACACACA-3' (27) (SEQ ID NO:2) was synthesized on a CPG
support employing the standard protocol.

5'-Fluorescein-CAC ACA CAC ACA CAC ACA CA-3' (SEQ ID NO:2) ≡

27

<u>Synthesis of 5'-TGTGTGTGTGTGTGTGTGTG-3' (22) (SEQ ID NO:1)</u>. The synthesis of oligonucleotide (22) was accomplished by the standard phosphoramidite method on a 8800 DNA/RNA synthesizer (Millipore) at 160 μmol scale. After the final detritylation and subsequent washing, an aliquot of CPG bound oligonucleotide (21) was removed, dried and deprotected by 27% aqueous NH_4OH for 15 hours at 55 °C. Anion exchange HPLC analysis demonstrated a purity of 78% (at 260 nm) of crude oligonucleotide (22).

<u>Synthesis 5'-diene-oligonucleotide (23)</u>. Synthesis of compound (23) was performed on a Millipore 8800 synthesizer in a fluidized bed conformation. The CPG bound oligonucleotide (21) (160 μmol) as described above was treated with amidite (16) (0.2 M in CH_3CN, 2.5 equiv.) and 4,5-dicyanoimidazole (1.0 M in CH_3CN, 16 equiv.) for 10 minutes followed by a second amidite (16) addition (0.2 M in CH_3CN, 1.5 equiv.) together with 4,5-dicyanoimidazole (1.0 M in CH_3CN, 16 equiv.) for 10 minutes. The support bound oligonucleotide was oxidized with I_2 in the presence of pyridine under standard conditions and detritylated by treatment with 10% dichloroacetic acid in CH_2Cl_2. Cleavage from the support and base deprotection was performed with 27% aqueous NH_4OH for 2 hours at 70 °C. The deprotection solutions were then cooled to 4 °C before the CPG was filtered and washed with DI water to recover the crude oligonucleotide product, compound (23).

An aliquot of the crude oligonucleotide product (800 μL) was loaded onto a DNAPac PA-100 4x250 mm anion exchange column at a concentration of 10.6 mg/mL. The product was eluted with a linear elution gradient employing a two-buffer system, where buffer A is 25 mM Trizma/1 mM EDTA (Trizma-EDTA) with 10% CH_3CN and buffer B is Trizma-EDTA with 10% CH_3CN and 1 M NaCl. A temperature of 80°C was

5   maintained throughout the purification. Appropriate purification fractions were consolidated and desalted on a Nap25 column. After desalting the oligonucleotide (23) (designated as "23, pure") was provided in deionized-water at a concentration of 1.1 OD/mL (86% purity by anion exchange HPLC). MALDI-MS: M^+ 6585.47 (6585.1 calcd).

10   In a second synthesis of oligonucleotide (23), CPG bound oligonucleotide (21) (25 μmol) was treated with amidite (16) (0.2 M in CH$_3$CN, 15 equiv.) and 4,5-dicyanoimidazole (1.0 M in CH$_3$CN, 16 equiv.) for 20 minutes. After oxidation and capping the CPG bound oligonucleotide was partitioned into two aliquots. The first aliquot (0.25 g, 6 μmol) was subjected to cleavage from the support and base

15   deprotection to give 17 mg, (450 OD) of crude (purity 60% by anion exchange HPLC) diene (DMT)-oligonucleotide (24) after drying. The second aliquot (0.80 g, 19 μmol) was detritylated prior to cleavage from the support and base deprotection to give 89 mg (2400 OD) of crude (61% purity by anion exchange HPLC purity) oligonucleotide (23) (designated as "23, crude").

20

Synthesis of 5'-[N-(3-maleimidopropionyl)-6-aminohexyl]-TGTGTGTGTGTGTGTGTG TG-3' DNA oligonucleotide (26). 2-Cyanoethyl-N,N'-diisopropyl-6-(4-methoxytrityl-amino)-hexylphosphoramidite* (0.2 M in CH$_3$CN, 10 equiv. each. Proligo Biochemie GmbH, Hamburg, Germany. Prod.# M010282) was coupled to CPG bound

25   oligonucleotide (21) (32 μmole) in the presence of 4,5-dicyanomidazole activator (1.0 M in CH$_3$CN, 16 equiv.) for 20 minutes. Standard oxidation and capping preceded the final monomethoxytrityl removal with 10% dichloroacetic acid in CH$_2$Cl$_2$. Cleavage and deprotection of the oligonucleotide from the support in 27% aqueous NH$_4$OH and consequential drying provided 155 mg (4200 OD) of crude amino-oligonucleotide (25)

30   (55% purity by anion exchangeHPLC).

    Amino-oligonucleotide (25) (2.6 μmol) was resuspended in DMF (2 mL). To this solution maleimide NHS-ester (18) (35 mg, 130 μmol, 50 equiv.) was added and the reaction was stirred at room temperature overnight then placed in speed vacuum to remove the solvent. The dried pellet was then resuspended in H$_2$O (1.5 mL) and loaded

34

5   onto four 1 mL G-25 spin columns to remove un-reacted (18) and side products from the

product of the reaction maleimide-oligonucleotide (26).

Detection of maleimide by fluorescence.

        Maleimide-oligonucleotide (26) (15 nmol, ca. 500 OD) was reacted with

10   deprotected 5-((2-and-3)-S-(acetylmercapto)succinoyl)amino)fluorescein) (SAMSA

fluorescein reagent). SAMSA fluorescein reagent was deprotected by addition of 0.1 M

NaOH (50 µL) to the protected SAMSA fluorescein reagent (500 µg) and subsequent

reaction at room temperature for 15 minutes followed by neutralization with 6 N HCl (0.7

µL) buffered with 0.5 M Na_2HPO_4-buffer (10 µL, pH = 7.0). The entire deprotected

15   SAMSA-fluorescein was added to compound (26) (20 µL, 15nmols) and incubated for 30

minutes at room temperature. Unreacted SAMSA-fluorescein was removed by loading of

the reaction mixture on a 1 mL G-25 spin column, preequilibrated with phosphate-buffed

saline. The product, fluorescein stained (26) (1,2 and 3 µL) was loaded on a 15%

polyacrylamide Tris borate EDTA (TBE) gel and scanned with the Typhoon Molecular

20   Dynamics' Scanner for detection. Surface bound fluorescein was excited with a green

laser followed by emission detection with a 526 nm filter (SP fluorescein filter). The

photomultiplier tube settings were 600 V, sensitivity set to normal and the focal plane

was set at the surface. The results are set forth in Figure 1. The presence of a fluorescent

signal demonstrates that (25) was successfully reacted with reagent (18) to create the

25   maleimide-oligonucleotide (26).

Synthesis of 5'-fluorescein-CACACACACACACACACACA-3' DNA oligonucleotide
(27) (SEQ ID NO:2). Two separate 1 µmole syntheses were performed on an Expedite

DNA/RNA synthesizer using the standard phosphoramidite protocol.5' Fluorescein-

30   phosphoramidite (0.1 M in CH_3CN, 11.2 equiv., available from Glen Research, VA,

USA. Prod.# 10 5901) was coupled to the CPG-bound 20mer in the presence of tetrazole

(0.25 M in CH_3CN, 102 equiv.) for 5 minutes. Deprotection in 27% aqueous NH_4OH

resulted in approximately 300 OD of crude product for anion exchange HPLC

purification. Purification utilizing a buffer system of 20 mM $NaClO_4$ with 20 mM

35   NaOAc and 10 vol-% CH_3CN (buffer A) and 600 mM $NaClO_4$ with 20 mM NaOAc and

5   10% vol CH₃CN (buffer B), resulted in 75.7 OD of oligonucleotide product (27) from

synthesis #1 (96.6% purity by anion exchange HPLC) and 79.3 OD of oligonucleotide

product (27) from synthesis #2 (80% purity by anion exchange HPLC). Both

oligonucleotides were desalted on Nap 10 columns and finally evaporated in a speedvac

vacuum concentrator.

10

Example 7. Functionalization of Glass Surfaces with Maleimide

        Scheme 8 illustrates the reaction of either glass slides or CPG with the maleimide-

silane 19. The maleimide functionality is introduced onto the glass slides and CPG by

condensation of maleimide-silane (19) with the glass surfaces.

15   **Scheme 8**

        The method used to detect maleimide functionalization of the glass surfaces

involves staining the glass surface with a thiol-containing fluorescein reagent, which

20   reacts with the surface-bound maleimide via a Michael-addition reaction, as illustrated in

Scheme 9. The presence of fluorescein bound to the surfaces can then be detected with a

Molecular Dynamics' Tyhpoon fluorescence Scanner using a green laser to excite the

surface-bound fluorescein followed by detection of emission using a 526nm filter.

                                        Scheme 9

25

36

5

<u>Pre-treatment of glass micro slides</u>. Procedure #1: Glass micro slides (Corning no. 2947, description: plain, pre-cleaned, 3 inch x 1 inch x 1 millimeter) were soaked in 2 N NaOH for 2 hours at ambient temperature, washed with water, soaked in boiling 2 N HCl for 1 hour, washed with water and methanol, and then dried under reduced pressure in a high

10 vacuum oven at 100° C for 2 hours. The slides were then allowed to cool in a vacuum desiccator until use. Procedure #2: Micro slides were soaked in 2 N HCl at ambient temperature for 2 hours then in boiling 2 N HCl for 1 hour, washed with water and methanol, and then dried under reduced pressure in a high vacuum oven at 100 °C for 2 hours. The slides were then allowed to cool in a vacuum desiccator until use.

15

<u>Maleimide functionalization of glass slides</u>. The micro slides (2 pre-treated according to procedure #1 and 2 pre-treated according to procedure #2) were placed upright into a slide chamber containing a 1% (v/v) solution of the maleimide-silane reagent (19) in toluene (25 mL). The amount of solution used was sufficient to soak only the lower half

20 (approximately 1.5 inches) of each slide. After 16 hours, one of the slides (pre-treated according to procedure #1) was removed from the chamber and washed sequentially with toluene, methanol, methanol/water (1:1, v/v), water, methanol/water (1:1, v/v), methanol and ethyl acetate (both sides of the slide were washed with 3x2 mL of each solvent by pipette). The slide was then allowed to air dry.

25

<u>Detection of surface-maleimide by fluorescence</u>. The slide was assayed for maleimide functionalization using a thiol-containing fluorescein reagent, 5-((2-(and-3)-S-(acetyl-mercapto)succinoyl)amino)fluorescein (SAMSA fluorescein, Molecular Probes). One side of the slide was completely covered with an activated solution of SAMSA

30 fluorescein (prepared from 10 mg in 1 mL of 0.1 M NaOH, 14 µL of 6 M HCl, 0.2 mL of 0.5 M sodiumphosphate buffer, pH = 7) and incubated at ambient temperature for 30 minutes. The slide was then soaked in 0.5 M sodium phosphate buffer, pH 7, for 30 minutes with agitation and blotted dry with a fine paper tissue. The slide was then placed on the surface of a Molecular Dynamics' Typhoon fluorescence scanner. Surface bound

35 fluorescein was excited with a green laser followed by emission detection with a 526 nm

5   filter (SP fluorescein filter). The photomultiplier tube settings were 600 V, sensitivity set

to normal and the focal plane was set at the surface.

The slide showed a strong response consistent with maleimide functionality

primarily on the lower half of the slide (Figure 2). The distinct line and intense response

at and below the halfway mark on the slide show that the maleimide functionalization of

10   the glass slide was successful. The slide also showed a weak response consistent with

maleimide functionality on the edges of the slide, possibly due to the contact with the

sides of the chamber, and slightly above the halfway mark where the slide may have

come in contact with the solution during addition or removal of the slide from the

chamber. After 19 hours in the solution of toluene containing maleimide-silane reagent

15   (19), the remaining slides were washed as described above and then treated with a 5 vol-

% solution of chlorotrimethylsilane in pyridine/THF (1:9, v/v) for 5 minutes to cap free

silanol groups. The slides were then washed with THF, methanol and ethyl acetate (both

sides of the slide were washed with 3x2 mL of each solvent by pipette), allowed to air dry

and were stored in the vacuum desiccator until use.

20

Pre-treatment of native CPG-500. Native CPG-500 was stirred in boiling 2 N HCl for 2

hours, then collected on a glass-fritted funnel, washed with water and methanol, and dried

under reduced pressure in a high vacuum oven at 100 °C for 2 hours. The CPG was then

allowed to cool in a vacuum desiccator until use.

25

Maleimide functionalization of CPG. CPG (0.75 g, pre-treated according to the

procedure described above) was stirred in a 1 vol-% solution of the maleimide-silane

reagent (19) in toluene (25 mL) for 51 hours. The CPG was then collected on a glass-

fritted funnel and washed sequentially with toluene, methanol, methanol/water (1:1, v/v),

30   water, methanol/water (1:1, v/v), methanol and ethyl acetate (3x10 mL of each solvent).

The powder was then treated with a 5 vol-% solution of chlorotrimethylsilane in

pyridine/THF (1:9, v/v) for 2 minutes to cap free silanol groups The CPG was then

washed with THF, methanol and ethyl acetate (3x10 mL of each solvent). The powder

was allowed to air dry in the funnel under suction for 5 minutes, transferred to a beaker

5   and placed in a vacuum desiccator for 44 hours. The light tan powder (0.6 g) was then

   stored in a –20 °C freezer until use.

      Detection of surface maleimide by fluorescence. The derivatized CPG was assayed for

      maleimide functionalization using the thiol-containing fluorescein reagent, 5-((2-(and-3)-

10   S-(acetylmercapto)succinoyl)amino)fluorescein (SAMSA fluorescein). The CPG (5 mg)

      was placed into a centrifuge tube, an activated solution of SAMSA fluorescein (0.5 mL)

      was added, the vial was shaken to mix the contents and then allowed to sit at ambient

      temperature for 30 minutes. Native CPG-500 (5 mg) was also placed into a centrifuge

      tube and treated with an activated solution of SAMSA fluorescein (prepared from 5 mg in

15   0.5 mL of 0.1 M NaOH, 7 μL of 6 M HCl, 0.1 mL of 0.5 M sodiumphosphate buffer, pH

      = 7) following the same procedure to serve as a control. After 30 minutes, the mixtures

      were centrifuged, the supernatants were removed by pipette, and the CPG samples were

      suspended in water. The resulting mixtures were centrifuged, the supernatants again

      removed by pipette, and the CPG samples resuspended in water. This procedure was

20   repeated until the supernatants were clear and colorless (total of 5 washes for each

      sample). Each powder was dispersed onto a clean sheet of plastic wrap that was folded to

      contain the powder. Both samples were then placed side by side on the surface of a

      Molecular Dynamics' Typhoon fluorescence scanner. Surface bound fluorescein was

      excited with a green laser followed by emission detection with a 526 nm filter (SP

25   fluorescein filter). The photomultiplier tube settings were 600 V, sensitivity set to

      normal and the focal plane was set at the surface. The CPG that was treated with

      maleimide-silane showed a strong response consistent with maleimide functionality,

      whereas the native CPG-500 control did not show a response (Figure 3). The intense

      response on the CPG treated with the maleimide-silane versus the native CPG-500

30   control shows that the maleimide functionalization of the CPG was successful.

      Example 8. Functionalization of Glass Surfaces with a Diene

              Scheme 10 illustrates the functionalization of glass slides and CPG with diene-

      silane (20) to provide support-bound dienes capable of undergoing Diels-Alder surface

35   immobilization of dienophiles. The diene functionality is introduced onto the glass slides


                                            39

5   and CPG by condensation of diene-silane (20) with the glass surfaces as shown in

Scheme 10.

Scheme 10

Glass slide
CPG

10   The method used to detect diene functionalized glass surfaces involves staining

the glass surfaces with a maleimide-containing fluorescein reagent, which reacts with the

surface-bound diene via a Diels-Alder addition reaction as illustrated in Scheme 11. The

presence of fluorescein bound to the surface can then be detected with a Molecular

Dynamics' Tyhpoon fluorescence scanner using a green laser to excite the surface-bound

15   fluorescein followed by detection of emission using a 526 nm filter.

Scheme 11

Glass slide

Fluorescein-maleimide

Functionalization of glass slides with diene-silane reagent (20). Glass micro slides (4),

pre-treated according to procedure #1 described in Example 7) were placed upright into a

20   slide chamber containing a 1 vol-% solution of the diene-silane reagent (20) in toluene

(25 mL). The amount of solution used was sufficient to soak only the lower half

(approximately 1.5 inch) of each slide. After 15 hours, a "T" was etched into the top,

5   right-hand corner of each slide as it was removed from the chamber. The slides were washed sequentially with toluene, methanol, methanol/water (1:1, v/v), water, methanol/water (1:1, v/v), methanol and ethyl acetate (both sides of each slide were washed with toluene (3x2 mL) by pipette and the remaining washes were done by soaking the slides in a petri dish containing 10 mL of the solvent). The slides were then

10   allowed to air dry and were treated with a 5 vol-% solution of chlorotrimethylsilane in pyridine/THF (1:9, v/v) for 2 minutes to cap free silanol groupsThe slides were then washed with THF, methanol and ethyl acetate (both sides of the slide were washed with 3x2 mL of each solvent by pipette), allowed to air dry and were stored in the vacuum desiccator until use.

15

Detection of surface diene by fluorescence. One of the slides was assayed for diene functionalization using fluorescein-5-maleimide (Molecular Probes). Briefly, one side of the slide was completely covered with a 10 mM solution of fluorescein-5-maleimide in N,N-dimethylformamide and incubated at 6 °C overnight. The slide was then washed

20   with water (4x10 mL) and blotted dry with a fine paper tissue. The slide was then placed on the surface of a Molecular Dynamics' Typhoon fluorescence scanner. Surface bound fluorescein was excited with a green laser followed by emission detection with a 526 nm filter (SP fluorescein filter). The photomultiplier tube settings were 600 V, sensitivity set to normal and the focal plane was set at the surface. The slide showed a strong response

25   consistent with diene functionality on the lower half of the slide (Figure 4). The distinct line and intense response at and below the halfway mark on the slide show that the diene functionalization of the glass slide was successful.

Diene functionalization of CPG. CPG (0.75 g, pre-treated according to the procedure

30   described in Example 7) was stirred in a 1 vol-% solution of the diene-silane reagent (20) in toluene (25 mL) for 52 hours. The CPG was then collected on a glass-fritted funnel and washed sequentially with toluene, methanol, methanol/water (1:1, v/v), water, methanol/water (1:1, v/v), methanol and ethyl acetate (3x10 mL of each solvent). The powder was then treated with a 5 vol-% solution of chlorotrimethylsilane in

35   pyridine/THF (1:9, v/v) for 2 minutes to cap free silanol groups The CPG was then

41

5   washed with THF, methanol and ethyl acetate (3x10 mL of each solvent). The powder
     was allowed to air dry in the funnel under suction for 5 minutes, transferred to a beaker
     and placed in a vacuum desiccator for 44 hours. The white powder (0.6 g) was then
     stored in a -20 °C freezer until use.

10   Detection of surface diene by fluorescence. The derivatized CPG was assayed for diene
     functionalization using fluorescein-5-maleimide (Molecular Probes). The CPG (5 mg)
     was placed into a centrifuge tube, a 10 mM solution of fluorescein-5-maleimide in DMF
     (0.5 mL) was added, the vial was shaken to mix the contents and incubated at 6 °C
     overnight. The mixture was then centrifuged, the supernatant was removed by pipette,
15   and the CPG sample was suspended in water. The resulting mixture was centrifuged, the
     supernatant again removed by pipette, and the CPG sample resuspended in water. This
     procedure was repeated until the supernatant was clear and colorless (total of 5 washes).
     The powder was dispersed onto a clean sheet of plastic wrap that was folded to contain
     the powder. Native CPG-500 (5 mg) was also treated with fluorescein-5-maleimide to
20   serve as a control. It was incubated in a 10 mM solution of fluorescein-5-maleimide in
     DMF (0.5 mL) for 2 hours at ambient temperature and then treated according to the
     procedure described above for the CPG treated with the diene-silane. Both samples were
     then placed side by side on the surface of a Molecular Dynamics' Typhoon fluorescence
     scanner. Surface bound fluorescein was excited with a green laser followed by emission
25   detection with a 526 nm filter (SP fluorescein filter). The photomultiplier tube settings
     were 600 V, sensitivity set to normal and the focal plane was set at the surface. The CPG
     that was treated with diene-silane showed a strong response consistent with diene
     functionality (Figure 5A), whereas the native CPG-500 control did not show a response
     (Figure 5B). The intense response on the CPG treated with the diene-silane versus the
30   native CPG-500 control show that the diene functionalization of the CPG was successful.

Example 9. Immobilization of Oligonucleotides via Diels-Alder Cycloaddition

     Scheme 12 illustrates the conjugation of diene oligonucleotide (23) to maleimide
functionalized glass slides and maleimide coated microtiter plates. The demonstration of

42

5   conjugation was achieved by hybridization with a labeled complementary sequence and the detection of fluorescence.

Scheme 12

Glass slide
Maleimide-coated
microtiter plates

hybridization

27

10   <u>Conjugation of diene-oligonucleotide (23) to maleimide functionalized glass slides</u>. Two maleimide coated slides (1 pre-treated according to procedure #1 and 1 pre-treated according procedure #2, as described in Example 7) were each equipped with 3 silicone rubber septa (standard taper 14/20) running linearly up the slides using plastic ties to firmly secure the septa to the slides. Two septa were affixed to the lower maleimide-

15   functionalized half of each slide and one septum was affixed to the upper non-functionalized half of each slide. The outline of the septa was etched into the slide that was pre-treated according to procedure #2. A 4 pmol/μL solution of 5'-diene-oligonucleotide (23), pure, in 100 mM Na_2HPO_4 buffer at pH = 6.5 (125 μL) was added to the septum placed at the bottom of each slide to demonstrate surface immobilization of

20   an oligonucleotide on micro slides. (Figure 6). A 4 pmol/μL solution of control oligonucleotide (22) (SEQ ID NO:1) in 100 mM Na_2HPO_4 buffer at pH = 6.5 (125 μL) was added to the septum placed in the middle of each slide as a control to check for potential non-specific binding of the oligonucleotide to the functionalized portion of the slide. A 4 pmol/μL solution of 5'-diene-oligonucleotide (23), pure, in 100 mM Na_2HPO_4

5　　buffer at pH = 6.5 (125 μL) was added to the septum placed at the top of each slide as a

control to check for potential non-specific binding of the (23) to the non-functionalized

portion of the slides. The slides were incubated for 1 hour at 37 °C and then the septa

were removed and the slides were soaked 3 times each in a petri dish containing TRIS-

buffered saline containing Tween® 20 (TBST) (10 mM TRIS-Cl, pH 8, 150 mM NaCl,

10　　0.1% Tween® 20).

Detection of oligonucleotide immobilization on glass slides. The slides, pulled from the

buffer solutions, were immediately (to prevent the slides from drying out) immersed in a

4 pmol/μL solution of complementary 5'-fluorescein-oligonucleotide (27) in 5X standard

15　　saline citrate (SSC) containing 0.1% sodium dodecyl sulfate (SDS) (750 mM NaCl, 75

mM Na citrate, pH = 7, 0.1% SDS) in a petri dish (ca. 10 mL). The slides were incubated

for 30 minutes at 55 °C and were then soaked 3 times each in a petri dish containing

TBST. The slides were then placed on the surface of a Molecular Dynamics' Typhoon

fluorescence scanner. The fluorescein was excited with a green laser followed by

20　　emission detection with a 526 nm filter (SP fluorescein filter). The photomultiplier tube

settings were 800 V, sensitivity was normal, and the focal plane was set at the surface.

The slides each showed a strong response where diene-oligonucleotide (23) came into

contact with the maleimide-functionalized portion of the glass slide (27) (Figure 7). The

two controls on each slide showed no response indicating the lack of non-specific binding

25　　of (22) to the maleimide-functionalized portion of the slide and the lack of non-specific

binding of (23) to the non-functionalized portion of the slide. The outlines of the septa

etched on the slide pre-treated according to procedure #2 (slide "2") are faintly visible in

the scan.

30　　Conjugation of diene-oligonucleotide (23) to maleimide coated microtiter plates. 200 μL

of either the 5'-diene-oligonucleotide (23), crude and pure, or control oligonucleotide (22)

were added to maleimide microtiter plates (Pierce Cat # 15150ZZ) at a concentration of

2.5 pmol/μL in 100 mM Na_2HPO_4 buffer at pH =5.5, 6.5 or 7.7 as indicated. A well

containing only 100 mM pH = 6.5 Na_2HPO_4 was also included as a control for non-

35　　specific binding of labeled complementary oligonucleotide (27). For conjugation via

44

5   Diels-Alder reaction the plates were incubated for 2 hours at 37 °C. Wells containing the

immobilized oligonucleotides were aspirated and washed 3 times with TBST (10 mM

Tris-Cl pH = 8.0, 150 mM NaCl, 0.1% Tween 20).

Detection of oligonucleotide immobilization on maleimide coated microtiter plates.

10   Equal molar amounts of labeled complementary oligonucleotide (27) were added to the

wells in 5 x SSC + 0.1% SDS (750 mM NaCl, 75 mM Na Citrate, pH = 7.0) and

hybridized at 55 °C for 30 minutes. Following hybridization all samples were washed

with TBST (3x200 mL). Plates and slides were placed on the surface of a Molecular

Dynamics Tyhpoon fluorescence scanner and the fluorescein was excited with a green

15   laser followed by emission detection with a 526 nm filter (SP fluorescein filter).

Photomultiplier tube settings were 800 V, sensitivity was set to normal and the focal

plane was set at the surface. Oligonucleotide immobilization was most efficient at pH =

6.5 as shown in Figure 8. The control oligonucleotide (22) set of reactions showed no

non-specific binding as did all the buffer controls. The maleimide functionalized slide

20   also demonstrates oligonucleotide immobilization as evident from the signal generated

only from the area on the slide that was reacted with the silane-maleimide reagent (19).

Example 10. Conjugation of 5'-Diene-Oligonucleotide (24) to Maleimide functionalized

CPG

25   Maleimide-CPG was incubated with oligonucleotide (24) to form the Diels-Alder

adduct as illustrated in Scheme 13. Immobilization was verified by photometric

determination of DMT after cleavage with acid.

Scheme 13

Titration of maleimide functionalized CPG with 5'-diene-oligonucleotide (24). A series
of increasing amounts of diene(DMT)-oligonucleotide (24) (see Table 2) in Na_2HPO_4
10   buffer (100 mM, pH = 6.5, 350 μL) was added to maleimide derivatized CPG (10 mg,
each), weighed each in centrifuge tubes. The mixtures were incubated at 37°C for 1 hour
under shaking (to keep an optimal mixing of CPG). Each of the mixtures was centrifuged
and the supernatant was removed by pipette. The CPG samples were suspended in water
(1 mL) and the resulting mixtures were centrifuged and the supernatants again removed
15   by pipette. This washing procedure was repeated three times for each sample before
drying in a speed vacuum concentrator. The results of this titration are depicted
graphically in Figure 9.

Time dependence of reaction between maleimide-CPG and diene(DMT)-oligonucleotide
20   (24). Six samples were prepared by addition of diene(DMT)-oligonucleotide (24) (37
nmol) to each of 6 tubes containing a solution of maleimide derivatized CPG (10 mg,
each) in Na_2HPO_4 buffer (100 mM, pH = 6.5, 100 μL), that had been pre-equilibrated at
37°C. The conjugation reaction was stopped after different time intervals (see Table 3)
by removal of supernatant solution of (24) and washing of the CPG as described above.
25   The results are depicted graphically in Figure 10.

5   Loading Determination. To each CPG containing tube a 3% solution of p-

toluenesulfonic acid in CH_3CN (0.75 mL) was added and the resulting mixture was

agitated for 1 minute. For determination of loading the absorbance @ 497 nm of the

supernatant was determined photometrically using the following equation:

$$L = \frac{V \cdot ABS}{m_{resin} \cdot \varepsilon \cdot d}$$

$V = 1 \text{ cm}^3$

$m_{resin} = 10 \text{ mg}$

$\varepsilon = 71,200 \text{ cm}^2/\text{mmol}$

$d = 1 \text{ cm}$

$$\boxed{L \text{ [umol/g]} = 1.4045 \cdot ABS}$$

10

Example 11. Conjugation of 5'-Maleimide-Oligonucleotide (26) to Diene coated Glass
Surfaces

Scheme 14 shows the conjugation of maleimide-oligonucleotide (26) with diene

functionalized glass surfaces. The demonstration of conjugation was achieved by

15   hybridization with the labeled complementary sequence (27) and the detection of

fluorescence as described above.

Scheme 14

Glass slide
CPG

26

hybridization

27

20   Conjugation of maleimide-oligonucleotide (26) to diene-functionalized glass slides. One

diene-coated slide was equipped with 3 silicone rubber septa (standard taper 14/20)

47

5   running linearly up the slide. The septa were compressed onto the slide between two 3 x

5 x ¼ inch pieces of acrylic sheet that were fastened together on both sides of the slide

using thumb screws. The upper acrylic sheet contained 3/16-inch holes directly above

the middle of the septa to allow needle-access to the septa. Two septa were affixed to the

lower diene-functionalized half of the slide and one septum was affixed to the upper non-

10   functionalized half of the slide. A 4 pmol/μL solution of maleimide-oligonucleotide (26)

in 100 mM Na$_2$HPO$_4$ buffer at pH = 6.5 (125 μL) was added to the septum placed at the

bottom of the slide to demonstrate surface immobilization of an oligonucleotide on a

micro slide. A 4 pmol/μL solution of control oligonucleotide (22) in 100 mM Na$_2$HPO$_4$

buffer at pH = 6.5 (125 μL) was added to the septum placed in the middle of the slide as a

15   control to check for potential non-specific binding of the oligonucleotide to the

functionalized portion of the slide. A 4 pmol/μL solution of maleimide-oligonucleotide

(26) in 100 mM Na$_2$HPO$_4$ buffer at pH = 6.5 (125 μL) was added to the septum placed at

the top of each slide as a control to check for potential non-specific binding of the

maleimide-oligonucleotide (26) to the non-functionalized portion of the slide. The slide

20   was incubated for 1 hour at 37 °C and then the septa were removed and the slide was

soaked 3 times each in a petri dish containing TRIS-buffered saline containing Tween®

20 (TBST) (10mM TRIS-Cl, pH = 8, 150 mM NaCl, 0.1% Tween® 20).

Detection of oligonucleotide immobilization on glass slides. The slide, pulled from the

25   buffer solution, was immediately (to prevent the slide from drying out) immersed in a 4

pmol/μL solution of complementary 5'-fluorescein-oligonucleotide (27) in 5X SSC

containing 0.1% SDS (10 mL) in a petri dish. The slide was incubated for 30 minutes at

55-60 °C. The slide was then soaked 3 times each in a petri dish containing TBST. The

slide was analyzed using the Molecular Dynamics Typhoon fluorescence scanner, but the

30   results indicated that the washing conditions were insufficient to remove non-specifically

bound oligonucleotide from the plate (Figure 11, slide "1"). The slide was then washed 3

times in a petri dish containing 1X PBS (phosphate-buffered saline solution) with 0.1%

SDS. The slide was again analyzed using the Molecular Dynamics Typhoon

fluorescence scanner and showed a strong response only where maleimide-

35   oligonucleotide (26) came into contact with the diene-functionalized portion of the glass

48

5   slide and then hybridized with (27) (Figure 11, slide "2"). The two controls on the slide

showed no response indicating that the washing conditions were sufficiently stringent to

remove non-covalently bound oligonucleotide (22) from the diene-functionalized portion

of the slide and non-covalently bound maleimide-oligonucleotide (26) from the non-

functionalized portion of the slide. The diene-functionalized portion of the slide (lower

10   half) shows some fluorescence outside of the area that was reacted with (26) indicating

there is some residual non-specific binding of (27) to the diene-functionalized portion of

the slide.

Conjugation of maleimide-oligonucleotide (26) to diene-functionalized CPG. Diene-

15   coated CPG (15 mg) was placed into a centrifuge tube. A 4 pmol/ μL solution of

maleimide-oligonucleotide (26) in 100 mM Na_2HPO_4 buffer at pH = 6.5 (125 μL) was

added, the vial was shaken to mix the contents, and then incubated for 1 hour at 37 °C.

The mixture was then centrifuged, the supernatant was removed by pipette, and the CPG

sample was suspended in TRIS-buffered saline containing Tween® 20 (TBST) (10 mM

20   TRIS-Cl, pH = 8, 150 μM NaCl, 0.1% Tween® 20). The resulting mixture was

centrifuged, the supernatant again removed by pipette, and the CPG sample resuspended

in TBST. This procedure was repeated for a total of 3 washes. In addition, two control

experiments were run following the above procedure. One of the control experiments

involved using control oligonucleotide (22) in place of compound (26) to check for

25   potential non-specific binding of the oligonucleotide to diene-functionalized CPG. The

other control experiment involved using non-functionalized CPG capped with

chlorotrimethylsilane as a control to check for potential non-specific binding of the

maleimide-oligonucleotide (26) to non-functionalized CPG.

30   Detection of oligonucleotide immobilization on CPG. A 4 pmol/μL solution of

complementary 5'-fluorescein-oligonucleotide (27) in 5X SSC containing 0.1% SDS

(125 μL) was immediately added to each of the CPG samples obtained after reaction with

maleimide-oligonucleotide (26) and washings. The samples were incubated for 30

minutes at 55-60 °C. The samples were then washed 3 times as described above with 1X

35   PBS (phosphate-buffered saline solution) with 0.1% SDS. After the final wash was

49

5   removed by pipette, each sample was dispersed onto a clean sheet of plastic wrap and the plastic wrap was folded to contain the powder. The three samples, individually wrapped, were then placed side-by-side on the surface of a Molecular Dynamics' Typhoon fluorescence scanner. The samples were analyzed using the Typhoon fluorescence scanner, but the results indicated that the washing conditions were insufficient to remove

10   non-specifically bound (26) from the diene-functionalized CPG (Figure 12A). The samples were then transferred back into their original centrifuge tubes and washed 3 times with 0.5X SSC + 0.1% SDS (significant loss of each sample occurred during transfers). The samples were then again dispersed onto sheets of plastic warp and analyzed using the Typhoon fluorescence scanner. The diene-functionalized CPG sample

15   that was treated with maleimide-oligonucleotide (26) showed a strong response after hybridization with 27 (Figure 12B, slide "2A"). The two controls showed comparatively little response indicating that the Diels-Alder surface immobilization of maleimide-oligonucleotides can be performed on diene-functionalized CPG.

20   <u>Example 12</u>. <u>Preparation of a Diene Modified Oligonucleotide</u>

        Scheme 15 illustrates the preparation of diene modified oligonucleotide (29) from N-hydroxysuccinimide ester (10), the synthesis of which is described in Example 2.

Scheme 15

$NH_2(CH_2)_6OPO_2$-5'-d(CTACCTACGATCTGACTAGC)-3'   10

28 (ODN99225) (SEQ ID NO:3)   sodium borate
(25 mM)
ACN

29   ≡

25

     5'-Amine modified oligodeoxynucleotide (28) (ODN99225) was prepared employing standard solid phase automated synthesis on controlled pore glass (CPG) via the phosphoramidite method . After deprotection and cleavage from the CPG support,

5   the crude amine-modified oligonucleotide was purified by preparative anion exchange

chromatography on a 200 mL Source 15Q column (quaternary ammonium

functionalized, monodisperse polystyrene beads) eluting with the gradient set forth in

Table 4.

Product containing fractions were combined and concentrated *in vacuo*. The

10   material was desalted by a HPLC-method which involved adsorbing the crude material

onto a C18 column in water, washing with a 1 M NaCl solution followed by water, then

eluting the material with EtOH. The amine oligonucleotide was coupled to N-

hydroxysuccinimide ester (10) in a mixture of 25 mM sodium borate buffer and

acetonitrile (40%) employing roughly 4 equivalents of compound (10). Analytical

15   reversed phase chromatography indicated a final product purity of 95.9%. Electrospray

mass spectrometric analysis confirmed the identity of the oligonucleotide conjugate (29)

(observed MW=6639.0; calcd MW=6639).

Example 13. HPLC Monitoring of a Diels-Alder Reaction Employing a Cyclohexadiene

20   Oligonucleotide

To confirm the Diels-Alder reactivity of diene conjugate (29), labeling with

commercially available maleimide dienophiles (30) (Aldrich) and (31) (Molecular

Biosciences) were carried out as illustrated in Scheme 16. Briefly, to a solution of (29)

(1.5 mM) in phosphate buffer (pH=6.8) were added 100 equivalents of compound (30) or

25   (31). The progress of the reaction was monitored by analytical anion exchange

chromatography with samples taken every 5 minutes (as described below). Treatment of

(29) with N-ethyl maleimide (30) resulted complete conversion to adduct (32) within 5

minutes, while biotin maleimide 31 required 20 minutes.

Scheme 16

N-Et Maleimide (**30**)
PEO3 Biotin maleimide
(**31**)

29

32 (R=Et)
33 (R=PEO₃ Biotin)

The progress of the Diels Alder reaction was monitored as follows: 2 μL of reaction solution was removed, treated with 8 μL of 0.1 M NaOH (to quench the maleimide), vortexed for 30 seconds and diluted with 50 μL of H_2O. Of this 60 μL

10   solution, 50 μL (~16.7 μg of oligonucleotide) was injected onto a 5 micron C18 Jupiter column. The samples were run using a buffer system of TEAA (pH 7.0; Eluent A) and acetonitrile (Eluent B) as outlined in Table 5.

Example 14. Preparation of diene modified polyethylene glycol substrates.

15   Scheme 17 illustrates the synthesis of a cyclohexadiene-PEG (34) .

Scheme 17

10

H_2N—| PEG |—OMe

34

$\equiv$ ⟨cyclohexadiene⟩—| PEG |

5   Diene (10) was treated sequentially with carbonyldiimidazole and methoxy

polyethylene glycol amine (MW=5000). The resulting carbamate product was purified

by careful dropwise addition into cold ether and collection of the precipitate by filtration.

The material obtained was used without further purification in surface immobilization

studies. Similarly, hydroxymethylanthracene (35) was converted to the analogous PEG

10   derivative (36) using the same method as illustrated in Scheme 18.

Scheme 18

Example 15. Preparation of a Maleimide-Coated Flow Cell for the BIAcore

Scheme 19 illustrates the preparation of a dienophile derivatized CM5 BIAcore

15   flow cell surface.

Scheme 19

The dienophile CM5 BIAcore flow cell surface was prepared by subjecting the

commercially available chip (coated with a matrix of carboxymethyl dextran) to a 3 step

20   derivatization procedure, as illustrated in Scheme 19. Briefly, the carboxy groups were

activated as the N-hydroxysuccinimide esters (via treatment with EDC/NHS), followed

by the addition of diamine linker (ethylene diamine, to provide a reactive primary amine

surface), which was treated with a commercially available bifunctional crosslinking

reagent. The resulting dienophile cell surface (37) was reproducibly prepared in this

5   manner as evidenced by the measurement of the Biacore sensorgram with each

experiment.

The sensorgrams were obtained using a BIAcore 2000 instrument (Pharmacia

Biosensor AB, Uppsala, Sweden. Lofas *et al.* (1991) Sens. Actuators B 5:79-84;

Malmqvist (1993) Nature 361:186-187.) employing a biosensor technique called "real-

10   time biomolecular interaction analysis" (BIA), which allows the real-time monitoring of

interactions between two or more molecules, such as proteins or nucleic acids and small

molecules, such as signaling substances and pharmaceuticals (Pharmacia Biosensor AB,

cf. http://www.biacore.com). The detection principle relies on the optical phenomenon of

"surface plasmon resonance" (SPR), which detects changes in the refractive index of the

15   solution close to the surface of the sensor chip (Brockman *et al.* (1999) J. Am. Chem.

Soc. 121:8044-8051 and references cited therein). This is in turn directly related to the

concentration of solute in the surface layer. To perform a BIA analysis, one interactant is

immobilized in a dextran matrix on the sensor chip, which forms one wall of a micro-

flow cell. Sample containing the other interactant(s) is then injected over the surface in a

20   controlled flow. Any change in surface concentration resulting from interaction is

detected as an SPR signal, expressed in resonance units (RU). The continuous display of

RU as a function of time, referred to as a Biacore sensorgram, thus provides a complete

record of the progress of association and dissociation.

Maleimide derivatization protocol (Khilko (1993) J. Bio. Chem. 268:15425-

25   15434):

Flow rate = 10 µL/min with pH 6.8 PBS running buffer

Injection sequence:

1. 40 µL of EDC-NHS mixture (from stock solutions: NHS at 11.5 mg/mL and

EDC at 75 mg/mL).

30   2. 100 µL of 1.0 M ethylenediamine diHCl at pH 6.0.

3. 100 µL of 25 mM sulfo-EMCS (NHS/maleimide bifunctional reagent in pH

6.8 running buffer. The overlaid Biacore sensorgrams depicted in Figure 13 show the

consistent results of this method.

54

5   Example 16. Comparison of Surface Derivatization via PEG-SH (Michael addition) vs
   PEG-Diene (Diels-Alder Surface Immobilization)

Scheme 20

10   By subjecting the dienophile flow cell surface described in Example 15 to MeO-
PEG-SH (MW=5000; pH=6.8 phosphate buffer, 10 μL/min flow rate), the functional
activity of the surface was confirmed as evidenced by the Biacore sensorgram depicted in
Figure 14.

        Likewise, addition of the PEG-diene substrate (34) prepared in Example 14
15   afforded the Biacore sensorgram depicted in Figure 15, confirming the dienophile
reactivity of the flow cell surface and suggesting that the relative rate of the Diels-Alder
surface immobilization is substantially slower than the Michael addition method
employing a PEG-thiol (12 hours vs 10 minutes).

20   Example 17. BIAcore Diels-Alder Reaction with Anthracene-PEG (36)

Scheme 21

        Reaction of dienophile derivatized CM5 BIAcore flow cell surface (37) with the
25   anthracene derivative (36) (preparation described in Example 14), using the method

55

5 described in Example 16, provided compound (38), which is described in the literature to have improved aqueous Diels-Alder reaction kinetics. Enhanced surface immobilization was observed using compound (36), compared to compound (34). As can be seen Figure 16, a comparable response was observed in approximately half the time.

10 Example 18. BIAcore Surface Immobilization of Diene Modified Oligonucleotide (29) via the Diels-Alder Conjugation and Hybridization with the Complementary Sequence

Surface immobilization of the cyclohexadiene modified oligonucleotide (29), followed by hybridization with the complementary oligonucleotide sequence is illustrated in Scheme 22. Briefly, the Diels-Alder reaction between dienophile (37) and diene (29)

15 was carried out using the method described in Example 16 to provide the immobilized oligonucleotide, compound (39). The sensorgram results are set forth in Figure 17. Immobilized oligonucleotide (39) was then hybridized with its complementary sequence using standard means. The Biacore sensorgram depicted in Figure 18, reveals an increased response upon association of the complementary oligonucleotide sequence to

20 the immobilized oligonucleotide, thus confirming the above immobilization technique.

Scheme 22

Example 19. Synthesis of Anthracene-Silane Reagent (42)

25 Scheme 23 illustrates the synthesis of an anthracene silane reagent for the functionalization of glass surfaces. Briefly, with reference to Scheme 23 hydroxymethylanthracene (35) was reacted with CDI to form imidazolate (41). Imidazolate (41) was then reacted with propylamino silane (17), to provide anthracene-

56

5   silane reagent (42), which was then used for glass derivatization as illustrated in Scheme
     24 below.

Scheme 23

10   <u>Synthesis of anthracene-silane reagent (42)</u>. To a stirring solution of (35) (4.8 mmol, 1.0
     g) in DMF (16 mL, 0.3 M) was added CDI (5.28 mmol, 0.856 g). After 3 hours, the
     reaction was pushed to completion by the addition of CDI (1.06 mmol, 0.171 g). The
     complete formation of the imidazolate (41) was confirmed by ^{1}H NMR, which showed
     that the methylene of the alcohol had shifted from 5.65 ppm to 6.45 ppm. This is

15   characteristic of the expected shift. To this stirring solution was added
     aminopropyltriethoxy silane (17) (4.8 mmol, 1.06 g). The reaction was placed under an
     argon atmosphere and allowed to stir overnight. The reaction was complete by ^{1}H NMR,
     which showed that the methylene of the imidazolate had shifted from 6.45 ppm to 6.15
     ppm, characteristic of conversion to the expected carbamate product (42).

20   To the NMR sample in CDCl$_3$ was added D$_2$O (200 μL). The tube was vortexed
     for 1 minute, and then a second ^{1}H NMR analysis was performed and revealed that
     compound (42) was still intact. As a result, the reaction solution was concentrated under
     reduced pressure at 40°C to a dark orange oil. The oil was dissolved in CH$_2$Cl$_2$ (250 mL)
     and washed with H$_2$O (150 mL). The organic phase was concentrated under reduced

25   pressure at 40°C to obtain a dark orange oil. Upon standing, the oil turned into a
     crystalline orange solid. ^{1}H NMR (300 MHz, CDCl$_3$) δ 8.46 (s, 1H), 8.37 (d, 2H, J = 9
     Hz), 7.99 (d, 2H, J = 8.4 Hz), 7.50 (m, 4H), 6.11 (s, 2H), 4.95 (br t, 1H), 3.75 (dd, 6H, J =
     10.5 and 14.1 Hz), 3.2 (dd, 2H, J = 10.3 and 13.2 Hz), 1.6 (m, 2H), 1.16 (t, 9H, J = 6.9
     Hz), 0.6 (t, 2H, J = 8.2 Hz). ^{13}C NMR (300 MHz, CDCl$_3$) δ 156.9, 131.6, 131.2, 129.2,

57

5   127.1, 126.8, 125.3, 124.4, 77.7, 77.3, 76.9, 59.2, 58.7, 43.8, 23.5, 18.5, 7.9. The crude

material was used, in the glass slide derivatization experiment illustrated in Example 20.

Example 20. Functionalization of Glass Slides with Anthracene-Silane Reagent (42)

Scheme 24 (Figure 19) illustrates the functionalization of glass microscope slides

10   with anthracene-silane reagent (42).

Scheme 24

glass slide
CPG

42

anthracene diene derivatized
glass substrate

One half of a clean microslide (not pre-treated, VWR) was dipped into a suspension of

15   reagent 42 (1.04 g) in toluene (50 mL) and CH_2Cl_2 (10 mL) for 1 hour. The slide was

then removed from the suspension and blotted dry on a piece of filter paper. The slide

was sonicated sequentially in toluene, toluene/ethanol (1:1, v/v) and ethanol (100 mL,

each). For drying the slide was placed in an oven at 80 °C overnight.

58

5   **Table 1. Known Methods for Immobilizing Biomolecules.**

Immobilization Chemistry	Reference	Process Time (conditions)
Hydrophobic (salt or detergent facilitated)	Nikifov et al. U.S. Patent No. 5,610,287 (1997)	overnight (RT)
Ionic (polylysine-coated microporous membrane+cDNA)	[1]Shalon et al. (1996) Brown et al. (1998)	2 hours (h) (80°C)
Disulfide formation	[2]Anderson et al.(1998) Rogers et al. (1999)	2 h (>2 µM; RT)
Epoxide opening with 3'-amino oligonucleotide	[3]Stimpson (acid cat; 1995) Beattie (elev temp; 1995) Lamture (KOH; 1994)	>1 h (50 µg/mL in PBS; RT)
Epoxide opening with 3'- or 5'-hydroxyl of oligonucleotide	[4]Shi et al. (base cat; 1999)	12+h (0.25-10 µM; 65°C)
Radical chemistry with –SH slides + underivatized oligonucleotides	Shi et al. (1999) (ref 4)	overnight (0.25-10 µM; RT)
Activated polypropylene or glass + amino oligodeoxyribonucleo-tides, PCR-products and PNA-oligomers; Surfaces activated as: a) isothiocyanate (phenyldiisothiocyanate) b) succinimidyl carbonate (DSC) c) succinimidyloxalate (DSO) d) dimethylsuberimidate	[5]Beier and Hoheisel (1999)	a)-d) overnight (0.1-1 µM, 37°C)
Gold surface + thioate oligonucleotides	[6]Beebe et al. (1995)	10+ hours (3-10 µg/mL; RT)
Carboxy oligonucleotides + amine slide	[7]Joos et al. (1997)	1 h (max 50% yield; pH=3.6; 0.05-50 pmol/15 µL; RT)
p-Nitrophenyl ester oligonucleotides + polylysine coated 96 well plates	[8]Nikiforov and Rogers (1995)	overnight (150-200 pmol/40-50 µL; RT)
Carboxy plates + amino oligonucleotides	Joos et al. (1997) (ref. 7)	overnight (10 pmol/well; RT)
Biotin cDNA+Strepavidin-coated 96 well plates	[9]Holmstrom et al. (1993)	30 minutes (RT)
Hydrazide gel (3D) + aldehyde oligonucleotide	[10]Yershov et al. (1996)	48 h (quantitative; 20°C)
Functionalized polyacrylamide gel matrices+ oligonucleotides: a) hydrazide gel/amino oligo	[11]Timofeev et al. (1996)	a) overnight (87%) b) 1.5 h (60-74% amine gel/ald oligo 94-97%

59

b) reductive amination (via NaCNBH$_3$, Me$_3$NBH$_3$ or PyrBH$_3$) c) 1° MsO-gel/amino oligo/K$_2$CO$_3$ d) glutaraaldehyde gel/amino oligonucleotides		aldehyde gel/amine oligo) c) overnight (35%) d) overnight (71%+17% non-specific binding) **Note**: All linkages were somewhat unstable in 0.1 M TEAA buffer (pH=7), 60°C; due to polymer degradation.
Maleimide surface/thiol oligonucleotides	[12]Chrisey *et al.* (1996)	5 min-8 h (0.1-0.5 µM; RT; 34-73%)
Isothiocyanate/amino oligonucleotides	[13]Guo *et al.* (1994)	1 h (0.1-20 mM; 37°C)
Amine 96 well plates/NHS ester oligonucleotides	[14]Running and Urdea (1990)	30 min (1.2 mM; RT)
Functionalized acrylamide derivatives/oligonucleotides a) bromoacetyl Biogel beads/thio oligonucleotides b) sulfhydryl beads (Biogel or trisacryl)/bromoacetyl oligonucleotides	[15]Fahy *et al.* (1993)	a) overnight (25 pmol/150 µL; pH 9; 5-43% yield) b) overnight (500 pmol/ mL, pH=9)
Activated carboxylate filter membrane (act. w/ EDC)/ amino oligonucleotides	[16]Zhang *et al.* (1991)	15 min-2 h (RT; pH=8.4; 80-90% attached w/ 90% specificity)
Boronic acid-modified protein/ hydroxamate modified protein (solution phase conjugation)	[17]Rogers *et al.* (1997)	30 min (RT)
Streptavidin agarose gel coated chip/ biotinylated cDNA	[18]Gilles *et al.* (1999)	120 s (electronic addressing)
Polystyrene or polycarbonate plates/anthraquinone oligos or cDNA with irradiation	[19]Koch *et al.* (1999)	10 min (0.3-20 µM)
Photochemical immobilization of anthraquinone-conjugated oliogonucleotides, DNA, and PCR amplicons on a variety of solid surfaces	[20]Koch *et al.* (2000)	15 min (irradiation)

[1]Shalon *et al.* (1996) Genome Research 639-645; Brown and Shalon (1998) U.S. Patent No. 5,807,522.
[2]Anderson and Rogers (1998) U.S. Patent No. 5,837,860; Rogers *et al.* (1999) Analytical Biochemistry 266:23-30.
[3]Stimpson *et al.* (1995) Proc. Natl. Acad. Sci. USA 92:6379-6383; Beattie *et al.* (1995) Clin. Chem. 41:700-706; Lamture *et al.* (1994) Nucleic Acids Research 22:2121-25.
[4]Shi and Boyce-Jacino (1999) U.S. Patent No. 5,919,626.
[5]Beier and Hoheisel (1999) Nucleic Acids Research 27(9):1970-1977.
[6]Beebe and Rabke-Clemmer (1995) U.S. Patent No. 5,472,881.

5   [7]Joos *et al.* (1997) Analytical Biochemistry <u>247</u>:96-101.
       [8]Nikiforov and Rogers (1995) Analytical Biochemistry <u>227</u>:201-209.
       [9]Holmstrom *et al.* (1993) Analytical Biochemistry <u>209</u>:278-283.
       [10]Yershov *et al.* (1996) Proc. Natl. Acad. Sci. USA <u>93</u>:4913-4918.
       [11]Timofeev *et al.* (1996) Nucleic Acids Research <u>24(16)</u>:3142-3148.
10   [12]Chrisey *et al.* (1996) Nucleic Acids Research <u>24(16)</u>:3031-3039.
       [13]Guo *et al.* (1994) Nucleic Acids Research <u>22 (24)</u>:5456-5465.
       [14]Running and Urdea (1990) BioTechniques <u>8 (3)</u>:276-277.
       [15]Fahy *et al.* (1993) Nucleic Acids Research <u>21(8)</u>:1819-1826.
       [16]Zhang *et al.* (1991) Nucleic Acids Research <u>19(14)</u>:3929-3933.
15   [17]Rogers *et al.* (1997) Gene Therapy <u>4</u>:1387-1392.
       [18]Gilles *et al.* (1999) Nature Biotechnolgy <u>17</u>:365.
       [19]Koch *et al.* (Exiqon) 1999.
       [20]Koch *et al.* (2000) Bioconjugate Chem. 11:474-483.

Table 2. Results from the Conjugation of Oligonucleotide (24) to maleimide CPG (Example 10)

Concentration of (24) [nmol/µL]	ABS [ ]	CPG-Loading [µmol/g]
0.30	0.549	0.771
0.37	0.583	0.819
0.44	0.655	0.920
0.52	0.718	1.008
0.67	0.847	1.190
0.74	0.896	1.258
0.93	1.013	1.423
1.10	1.199	1.684

Table 3. Time Dependence of the Rreaction Between Oligonucleotide (24) and Maleimide CPG (Example 10)

Reaction Time [min]	ABS []	CPG-Loading [µmol/g]
5	0.300	0.421
10	0.363	0.510
20	0.440	0.618
40	0.548	0.770
60	0.628	0.882
90	0.658	0.924

5

Table 4. Chromatography Conditions (Example 12)

Time (min)	%Eluent B	Gradient method
0	0	Linear
10	10	Linear
27	15	Linear

Buffer A: 25 mM Na_2HPO_3 solution (pH=7.5) with 10% EtOH.
Buffer B: 2M NaBr solution with 10% EtOH.

10

Table 5. Chromatography Conditions (Example 13)

Time (min)	%Eluent B	Gradient Method
0	0	Linear
21	30	Linear
22	100	Linear
32	100	Isocratic
33	0	Linear
42	0	Isocratic

Eluent A: TEAA (pH=7.0)
Eluent B: Acetonitrile